

OP 10U

TOP FEATURES

- To be used as backing flux
- Excellent back bead shape
- Easy slag removal

CLASSIFICATION

Flux	EN ISO 14174: SA CS 1
------	-----------------------

FLUX CHARACTERISTICS

Current type	AC; DC+
Grain size (EN-ISO 14174)	1-12
Redrying	300-350°Cx2-4h

PACKAGING AND AVAILABLE SIZES

Packaging	Weight (kg)	Item number
DRY BAG	25.0	W000400068

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application.

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing.
Please refer to www.lincolnelectric.eu for any updated information.