

VANDAL

TOP FEATURES

- Smooth and stable arc
- Well suited for positional welding (particularly vertical and overhead)
- Good slag removal even in narrow gaps

CLASSIFICATION

AWS A5.1 E7018-1 H4
EN ISO 2560-A E 42 4 B 32 H5

CURRENT TYPE

AC/DC+

WELDING POSITIONS

All positions, except vertical down

APPROVALS

ABS	LR	BV	RINA
+	+	+	+

CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, ALL WELD METAL

C	Mn	Si	P	S
0.08	1.2	0.4	≤0.020	≤0.015

MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Condition	Yield strength (MPa)	Tensile strength (MPa)	Elongation (%)	Impact ISO-V (J) -50°C
Typical values	AW	≥420	510-610	≥24	≥90

AW = As welded

OUTPUT RANGE

Diameter x Length (mm)	Current range (A)
2.5 x 350	65-95
3.2 x 450	85-135
4.0 x 450	110-210

PACKAGING AND AVAILABLE SIZES

Diameter x Length (mm)	Packaging	Electrodes/pack	Net weight/pack (kg)	Item number
2.5 x 350	CBOH	90	1.9	619167
	VPMD	90	1.9	619184
3.2 x 350	CBOH	54	1.9	619168
3.2 x 450	CBOH	54	2.4	619169
4.0 x 450	CBOH	40	2.7	619171

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing.
Please refer to www.lincolnelectric.eu for any updated information.