

# AISi5

## TOP FEATURES

- Good weldability, no porosity
- Shall be welded in DC+ mode

## CLASSIFICATION

AWS A5.3 E4043

## CURRENT TYPE

DC+

## WELDING POSITIONS

All positions, except vertical down

## CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, ALL WELD METAL

Al	Si
bal.	5.0

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Condition	0.2% Proof strength (MPa)	Tensile strength (MPa)	Elongation (%)
Typical values	AW	90	160	15

AW = As welded

## OPERATING CURRENT RANGE

Diameter x Length (mm)	Current range (A)
2.5 x 350	40-70
3.2 x 350	60-90

## AVAILABLE SIZES AND PACKAGING INFORMATION

Diameter x Length (mm)	Packaging	Electrodes/pack	Net weight/pack (kg)	Item number
2.5 x 350	CAN	-	2.0	800593
3.2 x 350	CAN	-	2.0	800609

## TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information.