

OUTERSHIELD® 71 ELITE

Mild Steel, All Position · AWS E71T-1C-H8, E71T-1M-H8, E71T-9C-H8, E71T-9M-H8

KEY FEATURES

- Smooth arc transfer and low spatter
- Designed for welding with either 100% CO₂ or 75-82% Argon/balance CO₂ shielding gases
- Good bead appearance
- Fast freezing slag for out-of-position welding
- Meets AWS D1.8 seismic lot waiver requirements

CONFORMANCES

AWS A5.20:	E71T-1C-H8, E71T-1M-H8, E71T-9C-H8, E71T-9M-H8
ABS:	3YSA H10
CWB/CSA W48:	E491T-9-H8, E491T-9M-H8
DNV - 2.9:	III YMS H10
Lloyd's Register:	3YS H10
AWS D1.8:	0.052", 1/16"

WELDING POSITIONS

All

SHIELDING GAS

100% CO₂
75 - 82% Argon / Balance CO₂
Flow Rate: 40 - 50 CFH

TYPICAL APPLICATIONS

- Shipbuilding, barges and offshore platforms
- Heavy equipment
- Structural fabrication
- General fabrication

DIAMETERS / PACKAGING

Diameter in [mm]	15 lb [6.8 kg] Plastic Spool 60 lb [27.2 kg] Master Carton	33 lb [15 kg] Steel Spool	60 lb [27.2 kg] Coil	600 lb [272 kg] Accu-Trak® Drum
0.045 [1.1]	ED029418	ED029201	ED029202	
0.052 [1.3]	ED029419	ED029204	ED029205	
1/16 [1.6]		ED029206	ED029207	ED029387

MECHANICAL PROPERTIES⁽¹⁾

Requirements	Yield Strength ⁽²⁾ MPa [ksi]	Tensile Strength MPa [ksi]	Elongation %	Charpy V-Notch J [ft-lbf]	
				@ -18°C [0°F]	@ -29°C (-20°F)
AWS A5.20 E71T-1C-H8, E71T-9C-H8 AWS A5.20 E71T-1M-H8, E71T-9M-H8	400 [58] min	485-655 [70-95]	22 min	27 [20] min –	– 27 [20] min
Typical Results ⁽³⁾ As-Welded with 100% CO ₂ As-Welded with 75% Ar/25% CO ₂	545-565 (79-82) 585-595 (85-87)	585-615 (85-90) 625-630 (91-92)	28 25-28	74-83 (55-61) 92-99 (68-73)	58-64 (43-47) 70-83 (52-61)

DEPOSIT COMPOSITION^{a)}

	%C	%Mn	%Si	%S	%P
Requirements AWS A5.20 E71T-1C-H8, E71T-9C-H8 AWS A5.20 E71T-1M-H8, E71T-9M-H8	0.12 max	1.75 max	0.90 max	0.03 max	0.03 max
Typical Results^{b)} As-Welded with 100% CO ₂ As-Welded with 75% Ar/25% CO ₂	0.01-0.04 0.02-0.04	1.41-1.50 1.55-1.65	0.44-0.60 0.56-0.75	≤0.01 ≤0.01	≤0.01 ≤0.01

TYPICAL OPERATING PROCEDURES

Diameter, Polarity Shielding Gas ^{c)}	CTWD ^{d)} mm [in]	Wire Feed Speed m/min [in/min]	Voltage (volts)	Approx. Current [amps]	Melt-Off Rate kg/hr [lb/hr]	Deposition Rate kg/hr [lb/hr]	Efficiency [%]
0.045 in [1.1 mm], DC+ 75% Ar / 25% CO ₂	25 [1]	4.5 [175]	21-24	130	1.7 [3.8]	1.5 [3.3]	87
		6.4 [250]	23-26	155	2.4 [5.4]	2.1 [4.7]	87
		7.6 [300]	24-27	180	2.9 [6.4]	2.5 [5.6]	87
		8.9 [350]	25-28	205	3.4 [7.6]	3.0 [6.6]	87
		10.2 [400]	26-29	230	4.0 [8.7]	3.5 [7.6]	87
		12.8 [500]	27-30	260	5.0 [10.9]	4.3 [9.5]	87
		15.3 [600]	28-31	290	6.0 [13.1]	5.2 [11.4]	87
0.052 in [1.3 mm], DC+ 75% Ar / 25% CO ₂	25 [1]	3.8 [150]	21-24	150	2.1 [4.6]	1.8 [3.9]	86
		5.1 [200]	22-25	180	2.8 [6.1]	2.4 [5.2]	86
		6.4 [250]	23-26	210	3.4 [7.6]	3.0 [6.5]	86
		7.6 [300]	24-27	240	4.8 [10.6]	4.1 [7.8]	86
		10.2 [400]	26-28	315	6.2 [13.7]	5.4 [10.5]	86
		12.8 [500]	28-31	335	6.9 [15.2]	6.0 [13.1]	86
1/16 [1.6 mm], DC+ 75% Ar / 25% CO ₂	25 [1]	3.2 [125]	21-24	190	2.4 [5.2]	2.0 [4.4]	85
		3.8 [150]	22-25	205	2.8 [6.2]	2.4 [5.3]	85
		5.1 [200]	22-26	240	3.8 [8.3]	3.2 [7.0]	85
		6.4 [250]	23-27	290	4.7 [10.3]	4.0 [8.8]	85
		7.6 [300]	24-28	325	5.6 [12.4]	4.8 [10.5]	85
		10.2 [400]	27-31	400	7.5 [16.5]	6.4 [14.0]	85

^{a)}Typical all weld metal. ^{b)}Measured with 0.2% offset. ^{c)}See test results disclaimer. ^{d)}When welding under CO₂, increase voltage by 1 Volt. ^{e)}To estimate ESO, subtract 1/4 in [6.0 mm] from CTWD.

Safety Data Sheets [SDS] and Certificates of Conformance are available on our website at www.lincolnelectric.com

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application.

CUSTOMER ASSISTANCE POLICY

The Lincoln Electric Company is manufacturing and selling high quality welding equipment, consumables, and cutting equipment. Our challenge is to meet the needs of our customers and to exceed their expectations. On occasion, purchasers may ask Lincoln Electric for information or advice about their use of our products. Our employees respond to inquiries to the best of their ability based on information provided to them by the customers and the knowledge they may have concerning the application. Our employees, however, are not in a position to verify the information provided or to evaluate the engineering requirements for the particular weldment. Accordingly, Lincoln Electric does not warrant or guarantee or assume any liability with respect to such information or advice. Moreover, the provision of such information or advice does not create, expand, or alter any warranty on our products. Any express or implied warranty that might arise from the information or advice, including any implied warranty of merchantability or any warranty of fitness for any customers' particular purpose is specifically disclaimed.

Lincoln Electric is a responsive manufacturer, but the selection and use of specific products sold by Lincoln Electric is solely within the control of, and remains the sole responsibility of the customer. Many variables beyond the control of Lincoln Electric affect the results obtained in applying these types of fabrication methods and service requirements.

Subject to Change – This information is accurate to the best of our knowledge at the time of printing. Please refer to www.lincolnelectric.com for any updated information.