

# Lincoln 71T1M

## TOP FEATURES

- Rutile gas shielded flux cored wire for welding with Ar-CO<sub>2</sub> shielding gas.
- Very good weldability in positional welding.
- CVN > 47J at -20°C.

## TYPICAL APPLICATIONS

- Fillet and butt welds in shipbuilding and general steel construction.

## CLASSIFICATION

AWS A5.20 E71T1-M  
EN ISO 17632-A T 42 2 P M 1 H5

## CURRENT TYPE

DC+

## WELDING POSITIONS

All except vertical down

## SHIELDING GASES (ACC. EN ISO 14175)

M21 Mixed gas Ar+ >15-25% CO<sub>2</sub>  
Flow rate 15-25 l/min

## APPROVALS

ABS	LR	DNV	RINA
3YSAH5	in development	III YMS(H5)	3Y S H5

## CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, ALL WELD METAL

Shielding gas	C	Mn	Si	P	S
M21	0,05	1,50	0,50	0,015	0,010

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition*	Yield strength (MPa)	Tensile strength (MPa)	Elongation (%)	Impact ISO-V (J) -20°C
Required: AWS A5.20			min. 400	490-660	min. 20	min. 27
EN ISO 17632-A			min. 420	500-640	min. 20	min. 47
Typical values	M21	AW	545	610	23	90

\* AW = As welded

## PACKAGING AND AVAILABLE SIZES

Wire diameter (mm)	Packaging	Weight (kg)	Item number
1.2	SPOOL (S200)	5.0	COARLC71TE23
	SPOOL (S300)	15.0	COARLC71TE21

### TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information.