

CITOFLEX GALVA

TOP FEATURES

- The best solution for robotic and semiautomatic welding of Zn coated steel
- Low spatter level and very regular bead appearance
- Improved quality of welds by optimized solidification time resulting in reduced level of porosity
- To be used with Ar/CO₂ gas shielding both on CV and pulsed modes.

CLASSIFICATION

AWS A5.18	E70C-GS
EN ISO 17632-A	T3T Z M M21 1 H15
EN ISO 17632-B	T43TG-1MS-H15

CURRENT TYPE

DC-

WELDING POSITIONS

All positions

SHIELDING GASES (ACC. EN ISO 14175)

M21	Mixed gas Ar+ 15-25% CO ₂
-----	--------------------------------------

APPROVALS

TÜV	DB
+	+

CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, ALL WELD METAL

C	Mn	Si	Al
0.4	1.2	0.3	<3

PACKAGING AND AVAILABLE SIZES

Wire diameter (mm)	Packaging	Weight (kg)	Item number
1.0	SPOOL (B300)	16.0	W000281064
1.2	SPOOL (B300)	16.0	W000281065
	DRUM	200.0	W000281066

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing. Please refer to www.lincolnelectric.eu for any updated information.