

SUPRANEL NiCu7

TOP FEATURES

- Typical specifications for the nickel-copper base metal are ASTM B127, B163, B164, B165, all of which have UNS Number N04400.
- The weld metal has a high corrosion resistance in saline solution and seawater.
- Suitable for joining and for surfacing of unalloyed or low-alloy steels and cast iron.

CLASSIFICATION

AWS A5.11 ENiCu-7
EN ISO 14172-A E Ni 4060

CURRENT TYPE

DC+

WELDING POSITIONS

All position, except vertical down

CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, ALL WELD METAL

C	Mn	Si	P	S	Ni	Cu	Fe	Ti	Al
0.08	3.5	1.2	0.01	0.005	63	30	1	0.9	0.03

MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Condition*	0.2% Proof strength (MPa)	Tensile strength (MPa)	Elongation (%)		Impact ISO-V (J) -30°C
				4d	5d	
Typical values	AW	not specified	≥480	≥30		not specified
	AW	≥200	≥410	not specified	≥27	not specified
	AW	320	520	40	35	110

* AW = As welded

OUTPUT RANGE

Diameter x Length (mm)	Current range (A)
2.5 x 300	50-70
3.2 x 350	75-100
4.0 x 350	90-130

PACKAGING AND AVAILABLE SIZES

Diameter x Length (mm)	Packaging	Electrodes/pack	Net weight/pack (kg)	Item number
2.5 x 300	VPMD	118	2.0	W100288087
3.2 x 350	VPMD	68	2.1	W100288088
4.0 x 350	VPMD	45	2.2	W000288089

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing.
Please refer to www.lincolnelectric.eu for any updated information.