

# 309S92 TIG

## TOP FEATURES

- High resistance to intergranular corrosion and general corrosion conditions.
- Ferrite number between 8-20
- Available in PE tube

## CLASSIFICATION

AWS A5.9M	ER309L
EN ISO 14343-A	W 23 12 L
EN ISO 14343-B	SS309L

## SHIELDING GASES (ACC. EN ISO 14175)

I1	Inert gas Ar (100%)
----	---------------------

## APPROVALS

TÜV

+

## CHEMICAL COMPOSITION (WEIGHT %), WIRE

	C	Mn	Si	S	P	Cr	Ni	Mo	Cu	FN
Min.		1.0	0.30			23.0	12.0			8
Max.	0.03	2.5	0.65	0.020	0.030	25.0	14.0	0.3	0.3	20
Typical	0.015	1.7	0.5	0.005	0.015	23.5	13	0.1	0.15	12

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

As welded	Typical
Tensile strength (MPa)	590
0.2% Proof strength (MPa)	450
Elongation (%) 4d	43
5d	41
Reduction of area (%)	55
Impact ISO-V (J) + 20°C	>200
- 20°C	
- 75°C	>150
Hardness, cap/mid HV	205/225

## PACKAGING AND AVAILABLE SIZES

Diameter x Length (mm)	Packaging	Weight (kg)	Item number
1.6	PE Tube	5.0	T309S92-16
2.0	PE Tube	5.0	T309S92-20
2.4	PE Tube	5.0	T309S92-24
3.2	PE Tube	5.0	T309S92-32

## TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing.  
Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information.