

CHROMET[®] 5

Low Alloy, Low Hydrogen · AWS E8015-B6 H4

KEY FEATURES

- B6 alloyed steel: 5% chromium, 0.5% molybdenum alloyed steel for elevated temperature service up to 600°C (1112°F)
- Designed for high strength and improved corrosion resistance in superheated steam, hot hydrogen gas and high sulphur crude oils
- Moisture resistant coating provides low amounts of weld metal hydrogen levels for a superior weld
- Weld metal chemistry is low in impurity elements allowing it to respect the X Factor (<15ppm) and J-factor (<120ppm)

WELDING POSITIONS

All, except vertical down

CONFORMANCES

AWS A5.5:	E8015-B6 H4
BS EN ISO 3580-A:	E CrMo5 B 3 2 H5
BS EN ISO 3580-B:	E 6216-5CM

TYPICAL APPLICATIONS

- Boiler Superheaters
- Heat Exchangers
- Piping
- Pressure Vessels
- Nitriding

DIAMETERS / PACKAGING

Diameter mm (in)	4.1kg (9.0lb) Can	4.2kg (9.3lb) Can	5.7kg (12.6lb) Can
2.5 [3/32]	Chromet5-25-1	Chromet5-32-1	Chromet5-40-1
3.2 [1/8]			
4.0 [5/32]			

MECHANICAL PROPERTIES⁽¹⁾ – As Required per AWS A5.5

	Yield Strength ⁽²⁾ MPa (ksi)	Tensile Strength MPa (ksi)	Elongation %	Charpy V-Notch J (ft-lbf)		Hardness HV
				@20°C (68°F)	@-10°C (14°F)	
Requirements AWS E8015-B6 H4	460 (67) min	550 (80) min	19	-	-	-
Typical Performance⁽³⁾ As-Welded	500 (73) min	610 (88) min	25	150 (111)	80 (59)	210

DEPOSIT COMPOSITION⁽¹⁾ – As Required per AWS A5.5

	%C	%Mn	%Si	%S	%P
Requirements AWS E8015-B6 H4	0.05-0.10	0.50-1.00	0.80 max	0.025 max	0.030 max
Typical Performance⁽³⁾	0.06	0.80	0.40	0.010	0.015
	%Cr	%Ni	%Mo	%Cu	
Requirements AWS E8015-B6 H4	4.0-6.0	0.40 max	0.45-0.65	0.3 max	
Typical Performance⁽³⁾	5.0	0.20	0.55	<0.1	

⁽¹⁾ Typical all weld metal ⁽²⁾ Measured with 0.2% offset ⁽³⁾ See test results disclaimer ⁽⁴⁾ Preferred polarity is listed first.

IMPORTANT: SPECIAL VENTILATION AND/OR EXHAUST REQUIRED

Fumes from the normal use of some welding products can contain significant quantities of components - such as chromium and manganese - which can lower the 5.0 mg/m³ maximum exposure guideline for general welding fume.

BEFORE USE, READ AND UNDERSTAND THE SAFETY DATA SHEET (SDS) FOR THIS PRODUCT AND SPECIFIC INFORMATION PRINTED ON THE PRODUCT CONTAINER.

TYPICAL OPERATING PROCEDURES

Polarity ⁽¹⁾	2.5 mm (3/32 in)	Current (Amps)	
		3.2 mm (1/8 in)	4.0 mm (5/32 in)
DC+	70-110	80-140	100-180

⁽¹⁾ Typical all weld metal ⁽²⁾ Measured with 0.2% offset ⁽³⁾ See test results disclaimer ⁽⁴⁾ Preferred polarity is listed first.

Safety Data Sheets (SDS) and Certificates of Conformance are available on our website at www.lincolnelectric.com

FUMES AND GASES can be hazardous to your health.

- Fumes from the normal use of this product contain significant quantities of potentially hazardous compounds. See consumable product label/insert.
- Keep your head out of the fumes.
- Use enough ventilation and local exhaust to keep fumes and gases from your breathing zone and the general area.
- An approved respirator should be used unless exposure assessments are below applicable exposure limits.

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application.

CUSTOMER ASSISTANCE POLICY

The Lincoln Electric Company is manufacturing and selling high quality welding equipment, consumables, and cutting equipment. Our challenge is to meet the needs of our customers and to exceed their expectations. On occasion, purchasers may ask Lincoln Electric for information or advice about their use of our products. Our employees respond to inquiries to the best of their ability based on information provided to them by the customers and the knowledge they may have concerning the application. Our employees, however, are not in a position to verify the information provided or to evaluate the engineering requirements for the particular weldment. Accordingly, Lincoln Electric does not warrant or guarantee or assume any liability with respect to such information or advice. Moreover, the provision of such information or advice does not create, expand, or alter any warranty on our products. Any express or implied warranty that might arise from the information or advice, including any implied warranty of merchantability or any warranty of fitness for any customers' particular purpose is specifically disclaimed.

Lincoln Electric is a responsive manufacturer, but the selection and use of specific products sold by Lincoln Electric is solely within the control of, and remains the sole responsibility of the customer. Many variables beyond the control of Lincoln Electric affect the results obtained in applying these types of fabrication methods and service requirements.

Subject to Change – This information is accurate to the best of our knowledge at the time of printing. Please refer to www.lincolnelectric.com for any updated information.