Lincolnweld® L-S3

Mild Steel Solid Electrode • AWS EH12K

Key Features

- A low carbon, high manganese, medium silicon electrode designed for use with the Lincolnweld® 800 series of neutral fluxes
- Capable of producing weld deposits with impact properties exceeding 27 J (20 ft•lbf) at -62°C (-80°F) when used with Lincolnweld® 888™, 8500™, and MIL800-H™ neutral fluxes

Conformances

AWS A5.17/A5.17M: 1997 EH12K EN 756: S3Si

Recommended Fluxes

Lincolnweld® 860®, 880M®, 882 $^{\text{\tiny TM}}$, 888 $^{\text{\tiny TM}}$, 8500 $^{\text{\tiny TM}}$, MIL800-H $^{\text{\tiny TM}}$, P223 $^{\text{\tiny TM}}$

DIAMETERS / PACKAGING

Diameter	60 lb (27.2 kg)
in (mm)	Coil
1/8 (3.2)	ED016767
5/32 (4.0)	ED016248

WIRE COMPOSITION(1) - As Required per AWS A5.17/A5.17M:1997

	%С	%Mn	%Si	%S	%P	%Cu
Lincolnweld® L-S3	0.06-0.15	1.50-2.0	0.25-0.65	0.025	0.025	0.35

Lincolnweld® LA-71

Mild Steel Solid Electrode • AWS EM14K

Key Features

- A low carbon, medium manganese, medium silicon electrode containing approximately 0.1% titanium
- Small addition of titanium allows deposits to be stress-relieved with little loss of strength, even with extended stress relief times
- Widely used with neutral basic fluxes in both as-welded and post-weld heat treated conditions

Conformances

AWS A5.17/A5.17M: 1997 EM14K EN 756: SZ

Recommended Fluxes

Lincolnweld® $860^{\$}$, 865^{\intercal} , $880M^{\$}$, 882^{\intercal} , 888^{\intercal} , 8500^{\intercal} , MIL800-H $^{\intercal}$, $960^{\$}$, $P223^{\intercal}$

DIAMETERS / PACKAGING

Diameter in (mm)	60 lb (27.2 kg) Coil	1000 lb (453 kg) Speed Feed® Drum
3/32 (2.4)	ED011052	
1/8 (3.2)	ED011051	EDS30781
5/32 (4.0)	ED011053	EDS30782

WIRE COMPOSITION(1) - As Required per AWS A5.17/A5.17M:1997

	%C	%Mn	%Si	%Ti	%S	%Р	%Cu
Lincolnweld® LA-71	0.06-0.19	0.90-1.40	0.35-0.75	0.03-0.17	0.025	0.025	0.35

⁽¹⁾Single values are maximums.

Material Safety Data Sheets (MSDS) and Certificates of Conformance are available on our website at www.lincolnelectric.com

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application.

CUSTOMER ASSISTANCE POLICY

The Lincoln Electric Company is manufacturing and selling high quality welding equipment, consumables, and cutting equipment. Our challenge is to meet the needs of our customers and to exceed their expectations. On occasion, purchasers may ask Lincoln Electric for information or advice about their use of our products. Our employees respond to inquiries to the best of their ability based on information provided to them by the customers and the knowledge they may have concerning the application. Our employees, however, are not in a position to verify the information provided or to evaluate the engineering requirements for the particular weldment. Accordingly, Lincoln Electric does not warrant or guarantee or assume any liability with respect to such information or advice. Moreover, the provision of such information or advice does not create, expand, or alter any warranty on our products. Any express or implied warranty that might arise from the information or advice, including any implied warranty of merchantability or any warranty of fitness for any customers' particular purpose is specifically disclaimed.

Lincoln Electric is a responsive manufacturer, but the selection and use of specific products sold by Lincoln Electric is solely within the control of, and remains the sole responsibility of the customer. Many variables beyond the control of Lincoln Electric affect the results obtained in applying these types of fabrication methods and service requirements.

Subject to Change - This information is accurate to the best of our knowledge at the time of printing. Please refer to www.lincolnelectric.com for any updated information.

