

P240

TOP FEATURES

- Fully basic agglomerated submerged-arc welding flux for multiple pass welding
- Excellent impact toughness properties.
- Low carbon burn-off.
- Recommended with Long stick-out process.

CLASSIFICATION

Flux	EN ISO 14174: S A FB 1 55 AC H5	
Flux/wire	EN ISO 14171-A: MR	AWS A5.17 / A5.23
P240 / L-61	S 42 4 FB S2Si	F7A6-EM12K
P240 / L-50M	S 46 6 FB S3Si	F7A8/P8-EH12K
P240 / LNS 160	S 46 6 FB S2Ni1*	F7A10/P10-ENi1-Ni1
P240 / LNS 162	S 46 6 FB S2Ni2*	F7A10/P10-ENi2-Ni2
P240 / LNS 165 (LA-85)	S 50 6 FB S3Ni1Mo0.2	F8A8/P8-ENi5-Ni5
P240 / LNS 168	S 69 4 FB S3NiCr2.5Mo	F10A5-EM2-M2

CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, ALL WELD METAL

Wire grade	C	Mn	Si	P	S	Mo	Ni	Cr
L-61	0.08	1.0	0.35	< 0.010	< 0.010			
L-50M (LNS 133U)	0.08	1.6	0.35	< 0.020	< 0.015			
LNS 160	0.08	1.0	0.25	< 0.020	< 0.015		0.9	
LNS 162	0.08	1.0	0.25	< 0.020	< 0.015		2.0	
LNS 165	0.08	1.3	0.35	< 0.020	< 0.015	0.15	0.9	
LNS 168	0.08	1.5	0.4	< 0.015	< 0.015	0.4	2.4	0.3

MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

Wire grade	Condition*	Yield strength (MPa)	Tensile strength (MPa)	Elongation (%)	Impact ISO-V (J)			
					-20°C	-40°C	-50°C	-60°C
L-61	AW	440	530	30	115	75	60	
L-50M (LNS 133U)	AW	460	560	28		110	90	70
L-50M (LNS 133U)	SR	400	540	28		120	110	90
LNS 160	AW	470	550	28				80
LNS 160	SR	430	490	32				100
LNS 162	AW	480	560	26				100
LNS 162	SR	460	530	30				140
LNS 165	AW	510	600	25		100		70
LNS 165	SR	490	580	24		110		70
LNS 168	AW	720	800	20			55	

* AW = As welded; SR = Stress relieved

FLUX CHARACTERISTICS

Current type	DC/AC
Basicity (Boniszewski)	3.1
Density (kg/dm ³)	1.1
Grain size (EN ISO 14174)	2 - 20

PACKAGING AND AVAILABLE SIZES

Packaging	Weight (kg)	Item number
SRB BAG	25.0	FXP240-25SRB

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing.
Please refer to www.lincolnelectric.eu for any updated information.