



Technical Specification Sheet

HARRIS LAg-5P-B BRAZING FILLER METAL

NOMINAL CHEMICAL COMPOSITION:

Silver	4.80 %
Phosphorus	6.41 %
Copper	Balance
Other Total	0.15 %

PHYSICAL PROPERTIES:

Solidus	1190°F (643°C)	Brazing Temperature Range	1300°-1500°F (704-816°C)
Liquidus	1420°F (785°C)		

BRAZING PROPERTIES:

This is a medium melting range silver brazing alloy designed for joining copper to copper and copper to brass. The alloy is ductile, and has a wide plastic range suitable for joining loose connections. However, at brazing temperature this alloy is quite fluid and suitable for tight fit-ups. Joint clearance recommendations are .002"-.006".

AVAILABLE FORMS:

Standard wire diameters, preformed rings

SPECIFICATION COMPLIANCE:

The Harris Products Group Internal Specification

RECOMMENDED FLUX:

No flux is required on copper

Use Stay-Silv white or black brazing flux with brasses

WARNING: PROTECT yourself and others. Read and understand this information.

FUMES AND GASES can be hazardous to your health.

HEAT RAYS (INFRARED RADIATION) from flame or hot metal can injure eyes.

- Before use, read and understand the manufacturer's instructions, Material Safety Data Sheets (MSDSs), and your employer's safety practices.
- Keep your head out of the fumes.
- Use enough ventilation, exhaust at the flame, or both, to keep fumes and gases from your breathing zone and the general area.
- Wear correct eye, ear, and body protection.
- See American National Standard ANSI Z49.1, *Safety in Welding, Cutting, and Allied Processes*, published by the American Welding Society, 550 N.W. LeJeune Road, Miami, Florida 33126; OSHA *Safety and Health Standards*, are published by the U.S. Government Printing Office, 732 North Capitol Street NW, Washington, DC 20401.

STATEMENT OF LIABILITY- DISCLAIMER

Any suggestion of product applications or results is given without representation or warranty, either expressed or implied. Without exception or limitation, there are no warranties of merchantability or of fitness for particular purpose or application. The user must fully evaluate every process and application in all aspects, including suitability, compliance with applicable law and non-infringement of the rights of others. The Harris Products Group and its affiliates shall have no liability in respect thereof.

Harris Products Group
A Lincoln Electric Company
4501 Quality Place
Mason, Ohio 45040 USA

Customer Service: 800-733-4533
800-733-4043
Technical Service: 800-733-5956
Facsimile: 513-754-8778

E-Mail: salesinfo@jwharris.com

techsupport@jwharris.com

For technical support and product information, visit our web site at www.harrisproductsgroup.com.