# Arosta® 316L

# **TOP FEATURES**

- Molybdenum level min. 2.7%
- High resistance to general and intergranular corrosion.
- Smooth weld appearance.
- Easy slag release.
- Strong electrode coating.

#### **CLASSIFICATION**

AWS A5.4 E316L-16 EN ISO 3581-A E 19 12 3 L R 12

## **CURRENT TYPE**

AC/DC(+/-)

#### **WELDING POSITIONS**

All position, except vertical down

## **APPROVALS**

ABS	LR	BV	DNV	ΤÜV	DB
+	+	+	+	+	+

## **CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, ALL WELD METAL**

С	Mn	Si	Cr	Ni	Мо	FN (acc. WRC 1992)
0.02	0.8	0.8	18.0	11.5	2.85	4-10

# MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Condition*	0.2% Proof strength (MPa)	Tensile strength (MPa)	Elongation (%)	Impac +20°C	t ISO-V (, -20°C	
Required: AWS A5.4		not specified	min. 490	min. 30	not specified		
EN ISO 3581-A		min. 320	min. 510	min. 25	not specified		
Typical values	AW	450	580	39		60	40

AW = As welded

#### **OUTPUT RANGE**

OUTFOTRANGE					
Diameter x Length (mm)	Current range (A)				
2.5 x 350	40-75				
3.2 x 350	60-110				
4.0 x 350	80-150				

## **PACKAGING AND AVAILABLE SIZES**

Diameter x Length (mm)	Packaging	Electrodes/pack	Net weight/pack (kg)	Item number
2.5 x 350	СВОН	90	2.0	529180-2
	VPMD	90	2.0	530001-2
3.2 x 350	VPMD	55	1.9	530032-2
	CBOX	120	4.2	529487-2
4.0 x 450	CBOX	81	5.5	529593-2

Arosta® 316L-EN-24/04/25



#### **TEST RESULTS**

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing. Please refer to  $\underline{\text{www.lincolnelectric.eu}} \text{ for any updated information.}$ 

Arosta® 316L-EN-24/04/25

