

Lincoln® 7016 DR

TOP FEATURES

- Excellent welding performance and highly stable and directional arc
- Very good gap bridging and ideally suited for root passes and positional welding
- Weldable on AC and DC
- Stable arc, also at low amperage
- Popular at welding schools

CLASSIFICATION

AWS A5.1 E7016-H8
EN ISO 2560-A E 42 2 B 1 2 H10

CURRENT TYPE

AC/DC +

WELDING POSITIONS

All position, except vertical down

APPROVALS

ABS

+

CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, ALL WELD METAL

C	Mn	Si	HDM
0.08	1.2	0.6	5 ml/100 g

MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Condition*	Yield strength (MPa)	Tensile strength (MPa)	Elongation (%)	Impact ISO-V (J)	
					+20°C	-30°C
Typical values	AW	≥ 380	470-600	26	≥ 150	≥ 60

AW = As welded

OUTPUT RANGE

Diameter x Length (mm)	Current range (A)
2.5x350	60-90
3.2x350	95-150
3.2x450	95-150
4.0x350	140-190

PACKAGING AND AVAILABLE SIZES

Diameter x Length (mm)	Packaging	Pieces / unit	Weight (kg)	Item number
2.5x350	CBOX	200	3.9	829275
3.2x350	CBOX	125	4.3	829276
3.2x450	CBOX	125	5.3	829277
4.0x450	CBOX	80	5.2	829278

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing.
Please refer to www.lincolnelectric.eu for any updated information.