FLUXINOX 308L PF

TOP FEATURES

- Fluxinox 308 L PF delivers welds with high corrosion resistance due to low carbon and balanced chemical composition.
- The best quality of welds with standard CV power sources helps to reduce investment expenditures.
- High productivity generates savings in total welding costs.

 Optimal semiautomatic process with high duty cycle.
- Savings in total welding cost resulting from reduced cleaning.
 Spatter free welds with easy slag removal.
- Higher overall performance and weldability comparing to solid wires and manual stick electrodes.
- Suitable for positional welding.

CLASSIFICATION

AWS A5.22 E308LT1-1

E308LT1-4

EN ISO 17633-A T 19 9 L P M21 1

T199LPC11

EN ISO 17633-B TS308L-FB1

CURRENT TYPE

DC+

WELDING POSITIONS

All positions

SHIELDING GASES (ACC. EN ISO 14175)

C1 Active gas 100% CO₂
M21 Mixed gas Ar+ 15-25% CO₂

APPROVALS

| LR | DNV | TÜV | | |
|----|-----|-----|--|--|
| + | + | + | | |

CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, ALL WELD METAL

| С | Mn | Si | Cr | Ni | Ferrite |
|-------|-----|-----|----|----|---------|
| ≤0.04 | 1.4 | 0.6 | 20 | 10 | 6-10 |

MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

| | Shielding gas | Condition* | Yield strength | Tensile strength | Elongation | Impact ISO-V (J) | |
|----------------|-----------------|------------|----------------|------------------|------------|------------------|--------|
| | Silieluling gas | Condition | (MPa) | (MPa) | (%) | -20°C | -196°C |
| Typical values | M21 | AW | ≥350 | ≥520 | ≥35 | ≥40 | ≥27 |

^{*} AW = As welded

Gas test: 82% Ar + 18% CO₂

PACKAGING AND AVAILABLE SIZES

| Wire diameter (mm) | Packaging | Weight (kg) | Item number | |
|-----------------------|---------------|----------------|-------------|--|
| 1.2 | SPOOL (BS300) | 15.0 | W000281261 | |



TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing. Please refer to www.lincolnelectric.eu for any updated information.

