

Zeron™ 100X SAW

TOP FEATURES

- Designed for strength and resistance to corrosion
- For welding of 25%Cr super duplex stainless steels
- Matching the proprietary Zeron 100 alloy
- Also used for joining supermartensitic stainless steels
- Superior resistance to stress corrosion cracking (SCC) and pitting corrosion

CLASSIFICATION

AWS A5.9M	ER2594
EN ISO 14343-A	S 25 9 4 N L

APPROVALS

ABS	DNV	TÜV
+	+	+

CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, WIRE

	C	Mn	Si	S	P	Cr	Ni	Mo	W	Cu	N	PREN
Typical	0.015	0.7	0.35	0.002	0.02	26	9.3	3.85	0.6	0.6	0.23	43

Pitting resistance equivalent Number PREN = Cr + 3.3Mo + 1.65W + 16N

MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

As welded	Units	Min.	Typical with SSB flux
Tensile strength	Mpa	760	885
0.2% Proof strength	Mpa	550	700
Elongation 4d	%	15	26
Elongation 5d	%	20	24
Reduction of area	%	-	48
Impact ISO-V -50°C	J	-	40
Hardness, cap/mid	HV	-	290

- = not specified

PACKAGING AND AVAILABLE SIZES

Wire diameter (mm)	Packaging	Weight (kg)	Item number
2.4	SPOOL	25.0	SAZ100X-24

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing. Please refer to www.lincolnelectric.eu for any updated information.