

UltraCore® 81Ni2A75-H

Low Alloy, All Position • AWS E81T1-Ni2M-JH4

Key Features

- ▶ Capable of producing weld deposits with impact toughness exceeding 41 - 89 J (30 - 66 ft•lbf) at -51°C (-60°F)
- ▶ Designed for welding with 75-85% Argon/ balance CO₂ shielding gas
- ▶ Premium arc performance and bead appearance
- ▶ H4 diffusible hydrogen levels
- ▶ ProTech® foil bag packaging

Typical Applications

- ▶ Mining
- ▶ Offshore
- ▶ Bridge fabrication
- ▶ High strength fabrication

Conformances

AWS A5.29/A5.29M: 2005	E81T1-Ni2M-JH4
ASME SFA-A5.29:	E81T1-Ni2M-JH4
ABS:	3YSA H5
Lloyd's Register:	3YS H5
DNV Grade:	III Y40MS H5
CWB/CSA W48-06:	E551T1-Ni2M-JH4 (E81T1-Ni2M-JH4)
EN ISO 17632-B:	T556T1-1MA-N5-H5

Welding Positions

All

Shielding Gas

75% - 85% Argon / Balance CO₂
Flow Rate: 40-55 CFH

DIAMETERS / PACKAGING

Diameter in (mm)	33 lb (15 kg) Spool*
0.045 (1.1)	ED032217
0.052 (1.3)	ED032277
1/16 (1.6)	ED032216

*Spool may be plastic or fiber.

MECHANICAL PROPERTIES⁽¹⁾ – As Required per AWS A5.29/A5.29M: 2005

	Yield Strength ⁽²⁾ MPa (ksi)	Tensile Strength MPa (ksi)	Elongation %	Charpy V-Notch J (ft•lbf)	
				@ -40°C (-40°F)	@ -51°C (-60°F)
Requirements⁽⁴⁾ - AWS E81T1-Ni2M-JH4	470 (68) min.	550-670 (80-100)	19 min.	27 (20) min.	27 (20) min.
Typical Results⁽³⁾ As-Welded with 75% Ar/25% CO ₂	555-580 (80-84)	615-635 (89-92)	25-28	69-115 (51-85)	41-89 (30-66)

UltraCore® 81Ni2A75-H

(AWS E81T1-Ni2M-JH4)

DEPOSIT COMPOSITION⁽¹⁾ – As Required per AWS A5.29/A5.29M: 2005

	%C	%Mn	%Si	%S
Requirements⁽⁴⁾ - AWS E81T1-Ni2M-JH4	0.12 max.	1.50 max.	0.80 max.	0.030 max.
Typical Results⁽³⁾ As-Welded with 75% Ar/25% CO ₂	0.04-0.05	0.93-1.05	0.25-0.28	0.005-0.006
	%P	%Ni	Diffusible Hydrogen (mL/100g weld deposit)	
Requirements⁽⁴⁾ - AWS E81T1-Ni2M-JH4	0.030 max.	1.75-2.75	4.0 max.	
Typical Results⁽³⁾ As-Welded with 75% Ar/25% CO ₂	0.006-0.008	2.01-2.13	3-4	

TYPICAL OPERATING PROCEDURES

Diameter, Polarity Shielding Gas	CTWD ⁽⁵⁾ mm (in)	Wire Feed Speed m/min (in/min)	Voltage (volts)	Approx. Current (amps)	Melt-Off Rate kg/hr (lb/hr)	Deposition Rate kg/hr (lb/hr)	Efficiency (%)	
0.045 in (1.1 mm), DC+ 75%-85% Ar/ balance CO ₂	25 (1)	All Position						86-88
		4.4 (175)	21-26	140	1.8 (4.0)	1.6 (3.5)		
		5.1 (200)	22-27	150	2.1 (4.6)	1.8 (4.0)		
		6.4 (250)	22-27	165	2.6 (5.7)	2.3 (5.0)		
		7.6 (300)	23-28	190	3.1 (6.8)	2.7 (6.0)		
		8.9 (350)	24-29	205	3.6 (8.0)	3.2 (7.0)		
		9.5 (375)	24-29	225	3.9 (8.6)	3.4 (7.5)		
		Flat & Horizontal						
		10.8 (425)	25-30	245	4.4 (9.7)	3.8 (8.5)		
		12.1 (475)	26-31	265	4.9 (10.8)	4.3 (9.5)		
12.7 (500)	27-32	275	5.2 (11.4)	4.5 (10.0)				
0.052 in (1.3 mm), DC+ 75%-85% Ar/ balance CO ₂	25 (1)	All Position						86-88
		3.8 (150)	21-26	150	2.0 (4.5)	1.8 (3.9)		
		4.7 (185)	22-27	165	2.5 (5.5)	2.2 (4.8)		
		5.7 (225)	22-27	190	3.1 (6.7)	2.7 (5.9)		
		6.4 (250)	23-28	215	3.4 (7.5)	2.9 (6.5)		
		7.0 (275)	23-28	235	3.7 (8.2)	3.2 (7.2)		
		7.6 (300)	24-29	255	4.1 (9.0)	3.5 (7.8)		
		Flat & Horizontal						
		8.5 (335)	24-30	275	4.5 (10.0)	4.0 (8.7)		
		9.5 (375)	25-31	295	5.1 (11.2)	4.4 (9.8)		
10.2 (400)	25-32	310	5.4 (12.0)	4.7 (10.4)				
1/16 in (1.6 mm), DC+ 75%-85% Ar/ balance CO ₂	25 (1)	All Position						86-88
		3.8 (150)	21-27	200	2.9 (6.3)	2.5 (5.5)		
		4.4 (175)	21-28	210	3.3 (7.4)	2.9 (6.4)		
		5.1 (200)	22-29	235	3.8 (8.4)	3.3 (7.3)		
		5.7 (225)	23-30	265	4.3 (9.5)	3.7 (8.2)		
		6.4 (250)	24-31	285	4.8 (10.5)	4.2 (9.2)		
		7.0 (275)	24-32	315	5.3 (11.6)	4.6 (10.1)		
		Flat & Horizontal						
		8.3 (325)	24-32	335	6.2 (13.7)	5.4 (11.9)		
		8.9 (350)	25-33	365	6.7 (14.7)	5.8 (12.8)		

⁽¹⁾Typical all weld metal. ⁽²⁾Measured with 0.2% offset. ⁽³⁾See test results disclaimer below. ⁽⁴⁾As-Welded with 75% Argon / 25% CO₂. ⁽⁵⁾To estimate ESO, subtract 1/4 in (6.0 mm) from CTWD.

Material Safety Data Sheets (MSDS) and Certificates of Conformance are available on our website at www.lincolnelectric.com

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application.

CUSTOMER ASSISTANCE POLICY

The Lincoln Electric Company is manufacturing and selling high quality welding equipment, consumables, and cutting equipment. Our challenge is to meet the needs of our customers and to exceed their expectations. On occasion, purchasers may ask Lincoln Electric for information or advice about their use of our products. Our employees respond to inquiries to the best of their ability based on information provided to them by the customers and the knowledge they may have concerning the application. Our employees, however, are not in a position to verify the information provided or to evaluate the engineering requirements for the particular weldment. Accordingly, Lincoln Electric does not warrant or guarantee or assume any liability with respect to such information or advice. Moreover, the provision of such information or advice does not create, expand, or alter any warranty on our products. Any express or implied warranty that might arise from the information or advice, including any implied warranty of merchantability or any warranty of fitness for any customers' particular purpose is specifically disclaimed.

Lincoln Electric is a responsive manufacturer, but the selection and use of specific products sold by Lincoln Electric is solely within the control of, and remains the sole responsibility of the customer. Many variables beyond the control of Lincoln Electric affect the results obtained in applying these types of fabrication methods and service requirements.

Subject to Change – This information is accurate to the best of our knowledge at the time of printing. Please refer to www.lincolnelectric.com for any updated information.