

Lincolnweld[®] H-560[™]

EN 760 – S A Z 3 • Alloy Flux

Typical Applications

- ▶ Use with Lincolnweld[®] L-60 mild steel wire for hardfacing

Packaging

100 lb (45.4 kg) Paper Bag	ED010345
----------------------------	----------

Key Features

- ▶ High alloy flux depositing primary carbides in a martensitic matrix
- ▶ Excellent material for severe abrasion applications
- ▶ Resistance to abrasion is 50 to 60 times that of plain carbon steel

NOTE: Deposit carbon, alloy content and hardness depend upon the ratio of flux melted to wire melted. High voltage promotes high carbon and alloy contents, while low voltage promotes lower carbon and alloy content.

Lincolnweld[®] 801[®]

EN 760 – S A FB 1; EN 760 – S A FB 2 • Neutral Flux

Packaging

50 lb (22.7 kg) Paper Bag	ED019588
550 lb (249 kg) Drum	ED023403
3000 lb (1361 kg) Bulk Bag	EDS30786

Key Features

- ▶ Provides smooth beads and excellent slag removal
- ▶ Fast-freezing

Typical Applications

- ▶ Hardfacing
- ▶ Use with Lincore[®] 20, 30-S, 35-S, 40-S, 42-S, 4130, 8620, 410, 410NiMo, 420 and 96S

NOTE: Deposit carbon, alloy content and hardness depend upon the ratio of flux melted to wire melted. High voltage promotes high carbon and alloy contents, while low voltage promotes lower carbon and alloy content.

Material Safety Data Sheets (MSDS) and Certificates of Conformance are available on our website at www.lincolnelectric.com

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application.

CUSTOMER ASSISTANCE POLICY

The Lincoln Electric Company is manufacturing and selling high quality welding equipment, consumables, and cutting equipment. Our challenge is to meet the needs of our customers and to exceed their expectations. On occasion, purchasers may ask Lincoln Electric for information or advice about their use of our products. Our employees respond to inquiries to the best of their ability based on information provided to them by the customers and the knowledge they may have concerning the application. Our employees, however, are not in a position to verify the information provided or to evaluate the engineering requirements for the particular weldment. Accordingly, Lincoln Electric does not warrant or guarantee or assume any liability with respect to such information or advice. Moreover, the provision of such information or advice does not create, expand, or alter any warranty on our products. Any express or implied warranty that might arise from the information or advice, including any implied warranty of merchantability or any warranty of fitness for any customers' particular purpose is specifically disclaimed.

Lincoln Electric is a responsive manufacturer, but the selection and use of specific products sold by Lincoln Electric is solely within the control of, and remains the sole responsibility of the customer. Many variables beyond the control of Lincoln Electric affect the results obtained in applying these types of fabrication methods and service requirements.

Subject to Change – This information is accurate to the best of our knowledge at the time of printing. Please refer to www.lincolnelectric.com for any updated information.