

CARBOFIL Ni1

TOP FEATURES

- Used for welding 1% Ni steels and fine grain steels.
- Ideal for low temperature applications.
- The weld metal contains less than 1% Ni, conforming to NACE requirements.

CLASSIFICATION

AWS A5.28 ER 80S-Ni1
EN ISO 14341-A G 46 6 M21 3Ni1

SHIELDING GASES (ACC. EN ISO 14175)

M21 Mixed gas Ar+ 15-25% CO₂

CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, WIRE

C	Mn	Si	P	S	Ni
0.08	1.1	0.6	≤0.020	≤0.020	0.9

MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition*	Yield strength (MPa)	Tensile strength (MPa)	Elongation (%)	Impact ISO-V (J)	
						+20 °C	-60 °C
Typical values	M21	AW	≥460	550-680	≥24	≥110	≥47

* AW = As welded

PACKAGING AND AVAILABLE SIZES

Wire diameter (mm)	Packaging	Weight (kg)	Item number
1.0	SPOOL (S300)	15.0	W000282973
	SPOOL (S300)	15.0	W000282975
1.2	SPOOL (B300)	16.0	W000282976
	DRUM	250.0	W000387299

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing. Please refer to www.lincolnelectric.eu for any updated information.