

Zeron™ 100X TIG

TOP FEATURES

- Designed for strength and resistance to corrosion
- Used for joining supermartensitic stainless steels
- Superior resistance to stress corrosion cracking (SCC) and pitting corrosion

CLASSIFICATION

AWS A5.9M ER2594
EN ISO 14343-A W 25 9 4 N L

SHIELDING GASES (ACC. EN ISO 14175)

I1 Inert gas Ar (100%)

APPROVALS

ABS	DNV	TÜV
+	+	+

CHEMICAL COMPOSITION (WEIGHT %), WIRE

	C	Mn	Si	S	P	Cr	Ni	Mo	W	Cu	N	PREN	PREW
Min.						24.0	9.0	3.5	0.5	0.5	0.2	40	40
Max.	0.03	1.0	1.0	0.01	0.03	26.0	10.0	4.0	1.0	1.0	0.3		
Typical	0.015	0.7	0.4	0.002	0.02	25	9.3	3.7	0.6	0.7	0.23	41	42

MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

Typical values as welded	Min.	TIG	TIG at 160°C
Tensile strength (MPa)	760	870	769
0.2% Proof strength (MPa)	550	695	523
Elongation (%)	4d	36	39
	5d	32	34
Reduction of area (%)		68	72
Impact ISO-V (J)	-50°C	130	
	-75°C	>100	
Hardness, cap/mid (HV)		290	

PACKAGING AND AVAILABLE SIZES

Diameter x Length (mm)	Packaging	Weight (kg)	Item number
1.6	PE Tube	2.5	TZ100X-16
2.0	PE Tube	5.0	TZ100X-20
2.4	PE Tube	5.0	TZ100X-24
3.2	PE Tube	5.0	TZ100X-32

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing.
Please refer to www.lincolnelectric.eu for any updated information.