# **SAFER G 48N**

## **TOP FEATURES**

- Easy to use even for fillet weld in vertical down position
- Flat or slightly convex beads and easy slag removal
- Working on poorly prepared pieces, pipes, tubes, etc.

## CLASSIFICATION

AWS A5.1 E6013 EN ISO 2560-A E 38 0 RC 11

## **CURRENT TYPE**

AC, DC-

## **WELDING POSITIONS**

All positions

## **APPROVALS**

| ABS | LR | BV | DNV | CE |
|-----|----|----|-----|----|
| +   | +  | +  | +   | +  |

## CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, ALL WELD METAL

| С    | Mn  | Si  | Р     | S     |
|------|-----|-----|-------|-------|
| 0.07 | 0.6 | 0.4 | ≤0.03 | ≤0.03 |

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

| Required       | Condition* | Yield strength<br>(MPa) | Tensile strength<br>(MPa) | Elongation<br>(%) | Impact ISO-V (J)<br>0°C |
|----------------|------------|-------------------------|---------------------------|-------------------|-------------------------|
| AWS A5.1       | AW         | ≥330                    | ≥430                      | ≥17               | not specified           |
| EN ISO 2560-A  | AW         | ≥380                    | 470-600                   | ≥20               | ≥47                     |
| Typical values | AW         | ≥420                    | 500-550                   | ≥24               | ≥47                     |

<sup>\*</sup>AW: As-welded

## **OUTPUT RANGE**

| Diameter x Length (mm) | Current range<br>(A) |
|------------------------|----------------------|
| 1.6 x 300              | 35-50                |
| 2.0 x 350              | 45-65                |
| 2.5 x 350              | 60-95                |
| 3.2 x 350              | 85-125               |
| 3.2 x 450              | 95-125               |
| 4.0 x 350              | 120-180              |
| 4.0 x 450              | 140-190              |
| 5.0 x 450              | 160-230              |

## **PACKAGING AND AVAILABLE SIZES**

| Diameter x Length<br>(mm) | Packaging | Electrodes/pack | Net weight/pack<br>(kg) | Item number |
|---------------------------|-----------|-----------------|-------------------------|-------------|
| 1.6 x 300                 | СВОН      | 240             | 1.6                     | W000384783  |
| 2.0 x 350                 | СВОН      | 160             | 1.9                     | W000384858  |
| 2.5 x 350                 | СВОН      | 120             | 2.1                     | W000384661  |
|                           | CBOX      | 260             | 4.5                     | W000258557  |
| 3.2 x 350                 | СВОН      | 65              | 1.8                     | W000384660  |
|                           | CBOX      | 160             | 4.4                     | W000258558  |
| 3.2 x 450                 | CBOX      | 160             | 5.6                     | W000258559  |
| 4.0 x 350                 | CBOX      | 105             | 4.5                     | W000258560  |
| 4.0 x 450                 | CBOX      | 105             | 5.8                     | W000258561  |
| 5.0 x 450                 | CBOX      | 67              | 6.1                     | W000384782  |

#### TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing. Please refer to <a href="www.lincolnelectric.eu">www.lincolnelectric.eu</a> for any updated information.