

OUTERSHIELD® 71M

Mild Steel, All Position ■ AWS E71T-9C-J, E71T-9M-J, E71T1-C1A4-CS1-H16, E71T1-M21A4-CS1-H16

KEY FEATURES

- Dual classified for both 100% CO₂ and 75% Argon / 25% CO₂ mixed gas
- Exceeds impact requirements at -40°C (-40°F)
- High travel speeds
- Spray like transfer with minimal spatter
- Rod based manufacturing for industry leading wire stiffness and feedability
- Increased rigidity allows for easy manual break-off

SHIELDING GAS

100% CO₂
75% Argon / 25% CO₂
Flow Rate: 40 - 50 CFH

WELDING POSITIONS

All, except vertical down

DIAMETERS / PACKAGING

Diameter in (mm)	10 lb (4.5 kg) Plastic Spool	25 lb (11.3 kg) Plastic Spool	33 lb (15 kg) Steel Spool	50 lb (22.7 kg) Coil
0.035 (0.9)	ED026804	ED026805		
0.045 (1.1)	ED020836	ED022659	ED030007	ED020844
0.052 (1.3)		ED022660	ED030008	ED020845
1/16 (1.6)		ED022661	ED030009	ED020846
Diameter in (mm)	300 lb (136 kg) Speed-Feed® Reel	500 lb (227 kg) Accu-Trak® Drum	600 lb (272 kg) Speed-Feed® Reel	
0.035 (0.9)				
0.045 (1.1)		ED027364		
0.052 (1.3)		ED029778		
1/16 (1.6)	ED020848	ED029779	ED020851	

MECHANICAL PROPERTIES⁽¹⁾

	Yield Strength ⁽²⁾ MPa (ksi)	Tensile Strength MPa (ksi)	Elongation %	Charpy V-Notch J (ft-lbf)		
				@ -18°C (0°F)	@ -29°C (-20°F)	@ -40°C (-40°F)
Requirements AWS E71T-1C-J / E71T-1M-J AWS E71T-9C-J / E71T-9M-J	400 (58) min	480-655 (70-95)	22 min	27 (20) min -	- 27 (20) min	27 (20) min ^(a) 27 (20) min ^(a)
Test Results⁽³⁾ As-Welded with 100% CO ₂ and 75% Argon/25% CO ₂	500-570 (72-83)	560-630 (81-91)	27-29	176-190 (130-140)	176-190 (130-140)	130-163 (96-120)

^(a)Electrodes with the optional supplemental designator "J" shall meet the minimum Charpy V-Notch impact energy requirement for its classification at a test temperature of 10°C lower than the test temperature for its classification.

CONFORMANCES

AWS A5.20:	E71T-1C-J, E71T-9C-J E71T-1M-J, E71T-9M-J
AWS A5.36:	E71T1-C1A4-CS1-H16 E71T1-M21A4-CS1-H16
ASME SFA-A5.20:	E71T-1C-J, E71T-9C-J E71T-1M-J, E71T-9M-J
ABS*:	3YSA H15
Lloyd's Register:	3YS H15
DNV Grade:	III YMS H10
BV Grade:	SA3YH (CO ₂ only)
CWB/CSA W48-06:	E491T-9, E491T-9M
EN ISO 17632-B:	T494T1-1MA-H15 T494T1-1CA-H15
MIL-E-24403/1:	MIL-71T-1C, MIL-71T-1M

*Only for 0.045, 0.052 and 1/16 in. diameters

TYPICAL APPLICATIONS

- Bridge, ship, & barge
- General fabrication
- Machinery fabrication
- Structural fabrication
- Offshore applications

DEPOSIT COMPOSITION⁽¹⁾

	%C	%Mn	%Si	%S	%P
Requirements AWS E71T-1C-J / E71T-1M-J AWSE71T-9C-J / E71T-9M-J	0.12 max	1.75 max	0.90 max	0.03 max	0.03 max
Test Results⁽³⁾ As-Welded with 100% CO ₂ and 75% Argon/25% CO ₂	0.05-0.07	1.04-1.60	0.25-0.50	≤ 0.01	< 0.01

TYPICAL OPERATING PROCEDURES

Diameter, Polarity Shielding Gas ⁽⁴⁾	CTWD ⁽⁵⁾ mm (in)	Wire Feed Speed m/min (in/min)	Voltage (volts)	Approx. Current (amps)	Melt-Off Rate kg/hr (lb/hr)	Deposition Rate kg/hr (lb/hr)	Efficiency (%)
0.035 in (0.9 mm), DC+ 100% CO ₂	19-25 (3/4-1)	5.1 (200)	20-23	95	1.3 (2.8)	1.1 (2.8)	85
		6.4 (250)	21-24	115	1.6 (3.5)	1.4 (3.5)	85
		7.6 (300)	22-25	130	1.9 (4.2)	1.6 (4.2)	86
		8.9 (350)	23-26	150	2.2 (4.9)	1.9 (4.9)	86
		10.2 (400)	24-27	160	2.6 (5.6)	2.2 (5.6)	86
		12.7 (500)	26-29	185	3.2 (7.0)	2.7 (7.0)	86
		15.2 (600)	28-31	200	3.8 (8.4)	3.3 (8.4)	86
		17.8 (700)	30-33	215	4.4 (9.8)	3.8 (9.8)	86
0.045 in (1.1 mm), DC+ 100% CO ₂	19-25 (3/4-1)	5.1 (200)	23-26	165	2.1 (4.6)	1.8 (3.9)	83
		6.4 (250)	24-27	190	2.6 (5.8)	2.2 (4.8)	84
		7.6 (300)	25-28	220	3.1 (6.9)	2.6 (5.8)	84
		8.9 (350)	26-29	245	3.7 (8.1)	3.1 (6.8)	84
		10.2 (400)	26-29	265	4.2 (9.2)	3.5 (7.8)	84
		12.7 (500)	28-31	295	5.2 (11.5)	4.4 (9.7)	84
		15.2 (600)	30-33	315	6.3 (13.8)	5.3 (11.7)	85
		17.8 (700)	32-35	325	7.3 (16.1)	6.2 (13.7)	85
0.052 in (1.3 mm), DC+ 100% CO ₂	19-25 (3/4-1)	3.8 (150)	22-25	150	2.1 (4.7)	1.7 (3.8)	81
		5.1 (200)	23-26	180	2.8 (6.2)	2.3 (5.1)	83
		6.4 (250)	24-27	210	3.5 (7.7)	2.9 (6.5)	83
		7.6 (300)	25-28	235	4.2 (9.3)	3.5 (7.8)	84
		8.9 (350)	27-30	265	4.9 (10.8)	4.2 (9.1)	84
		11.4 (450)	29-32	305	6.3 (13.9)	5.4 (11.8)	85
		12.7 (500)	30-33	325	7.0 (15.5)	6.0 (13.2)	85
		15.2 (600)	33-36	360	8.4 (18.6)	7.2 (15.8)	85
1/16 in (1.6 mm), DC+ 100% CO ₂	19 (3/4)	3.2 (125)	23-26	205	2.5 (5.4)	2.0 (4.5)	82
		3.8 (150)	24-27	225	3.0 (6.5)	2.4 (5.4)	82
		5.1 (200)	25-28	260	4.0 (8.7)	3.3 (7.2)	83
		6.4 (250)	26-29	295	4.9 (10.9)	4.1 (9.1)	83
		7.6 (300)	28-31	330	5.9 (13.0)	5.0 (10.9)	84
	25 (1)	10.2 (400)	30-33	395	7.9 (17.4)	6.6 (14.6)	84
		12.7 (500)	33-36	445	9.9 (21.7)	8.3 (18.3)	84

⁽¹⁾Typical all weld metal. ⁽²⁾Measured with 0.2% offset. ⁽³⁾See test results disclaimer ⁽⁴⁾When welding under mixed gas, decrease voltage. ⁽⁵⁾To estimate ESO, subtract 1/4 in (6.0 mm) from CTWD.
NOTE: This product contains micro-alloying elements.

Material Safety Data Sheets (MSDS) and Certificates of Conformance are available on our website at www.lincolnelectric.com

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application.

CUSTOMER ASSISTANCE POLICY

The Lincoln Electric Company is manufacturing and selling high quality welding equipment, consumables, and cutting equipment. Our challenge is to meet the needs of our customers and to exceed their expectations. On occasion, purchasers may ask Lincoln Electric for information or advice about their use of our products. Our employees respond to inquiries to the best of their ability based on information provided to them by the customers and the knowledge they may have concerning the application. Our employees, however, are not in a position to verify the information provided or to evaluate the engineering requirements for the particular weldment. Accordingly, Lincoln Electric does not warrant or guarantee or assume any liability with respect to such information or advice. Moreover, the provision of such information or advice does not create, expand, or alter any warranty on our products. Any express or implied warranty that might arise from the information or advice, including any implied warranty of merchantability or any warranty of fitness for any customers' particular purpose is specifically disclaimed.

Lincoln Electric is a responsive manufacturer, but the selection and use of specific products sold by Lincoln Electric is solely within the control of, and remains the sole responsibility of the customer. Many variables beyond the control of Lincoln Electric affect the results obtained in applying these types of fabrication methods and service requirements.

Subject to Change – This information is accurate to the best of our knowledge at the time of printing. Please refer to www.lincolnelectric.com for any updated information.

THE LINCOLN ELECTRIC COMPANY
22801 St. Clair Avenue ■ Cleveland, OH ■ 44117-1199 ■ U.S.A.
Phone: +1.216.481.8100 ■ www.lincolnelectric.com

