Lincoln[®] Pipe 8

Low Alloy, Cellulosic, Pipe · AWS E8010-P1

KEY FEATURES

- Excellent performance during vertical down and out of position welding.
- Deep penetration.
- Q2 Lot[®] certificates showing actual deposit chemistry and mechanical properties.
- Clear weld puddle without slag interference.
- Superior puddle control.

WELDING POSITIONS

All

TYPICAL APPLICATIONS

- Root pass on up to X80 grade pipe.
- Hot, fill and cap pass on up to X70.

CONFORMANCES

AWS A5.5: 2014	E8010-P1, E8010-G
ASME SFA-5.5	E8010-P1, E8010-G
ABS:	E8010-P1, E8010-G

DIAMETERS / PACKAGING

Diam	neter	Len	ght	Plastic tube 13.23 lb (6 kg)	Plastic tube 14.33 lb (6.5 kg)
in	(mm)	in	(mm)	Master Carton 39.68 lb (18 kg)	Master Carton 43 lb (19.5 kg)
1/8 5/32 3/16	3.25 4.00 5.00	14 14 14	355 355 355	504292 504294	

MECHANICAL PROPERTIES⁽¹⁾ – As Required per AWS A5.5:2014

	Yield Strength ⁽²⁾ Mpa (ksi)	Tensile Strength Mpa (ksi)	Elongation %		V-Notch :·lbf) @-40°C (-40°F)
Requirements AWS E8010 - P1	460 (67) min.	550 (80) min.	19 min.	27 (20) min.	not specified
Typical Results ⁽³⁾ - As-Welded	475 - 545 (69 - 79)	560 - 670 (81 - 97)	19 - 32	49 - 149 (36 - 110)	41 - 119 (30 - 88)

DEPOSIT COMPOSITION⁽¹⁾ – **As Required per** AWS A5.5:2014

	%С	%Mn	%Si	%P	%5
Requirements AWS E8010 - P1	0.20 max	1.20 max.	0.60 max.	0.03 max.	0.03 max.
Typical Results ⁽³⁾ - As-Welded	0.09 - 0.20	0.55 - 0.98	0.07 - 0.27	0.01 - 0.02 0.01 - 0.02	
				%V	
	%Ni	%Cr	%Mo	%	SV
Requirements AWS E7010 - P1	%Ni 1.00 max.	%Cr 0.30 max.	%Μο 0.50 max.	% 0.10	

TYPICAL OPERATING PROCEDURES

Polarity	1/8 in. (3.25mm)	Current (Amps) 5/32 in. (4.00 mm)	3/16 in. (5.00 mm)
CD+	65 - 120	100 - 165	130 - 210

Safety Data Sheets (SDS) and Certificates of Conformance are available on our website at www.lincolnelectric.com

FUMES AND GASES can be hazardous to your health.

· Fumes from the normal use of this product contain significant quantities of potentially hazardous compounds. See consumable product label/insert.

· Keep your head out of the fumes.

· Use enough ventilation and local exhaust to keep fumes and gases from your breathing zone and the general area.

· An approved respirator should be used unless exposure assessments are below applicable exposure limits.

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application.

CUSTOMER ASSISTANCE POLICY

The Lincoln Electric Company is manufacturing and selling high quality welding equipment, consumables, and cutting equipment. Our challenge is to meet the needs of our customers and to exceed their expectations. On occasion, purchasers may ask Lincoln Electric for information or advice about their use of our products. Our employees respond to inquiries to the best of their ability based on information provided to them by the customers and the knowledge they may have concerning the application. Our employees, however, are not in a position to verify the information provided or to evaluate the engineering requirements for the particular weldment. Accordingly, Lincoln Electric does not warrant or guarantee or assume any liability with respect to such information or advice. Moreover, the provision of such information or advice does not create, expand, or alter any warranty on our products. Any express or implied warranty that might arise from the information or advice, including any implied warranty of merchantability or any warranty of fitness for any customers' particular purpose is specifically disclaimed. Lincoln Electric is a responsive manufacturer, but the selection and use of specific products sold by Lincoln Electric as old y Lincoln Electric affect the results obtained in applying these types of fabrication methods and service requirements.

Subject to Change – This information is accurate to the best of our knowledge at the time of printing. Please refer to www.lincolnelectric.com for any updated information.



LINCOLN ELECTRIC MEXICANA S.A. DE C.V. Calz. Azcapotzalco La Villa 869, Industrial Vallejo • México, D.F. • C.P. 02300 • México. Phone: +52.55.5063.0030 • www.lincolnelectric.com.mx