

# OP 90W

Low Alloy Flux - EN ISO 14174- S A FB 155 DC H5

### KEY FEATURES

- Special agglomerated flux for welding P91 and P92 high creep resistant steels
- Flux provides a maximum resistance to hot cracking at high interpass temperatures
- Flux from drybag can be used without re-drying (300-350°C)

### PRODUCT INFORMATION

Basicity Index: 3

### TYPICAL APPLICATIONS

- Heat Exchangers
- Pressure Vessels
- Oil Refineries
- Boiler superheater tubing

### RECOMMENDED WIRES

Low Alloy Electrode  
OE-S1 CrMo91, OE-S1 CrMo92, 9CRMOV, 9CRMOV-N, 9CRWV

### PACKAGING

25 lb (55 kg) DryBag                      W000374906

### AWS TEST RESULTS

	Weld Condition	Yield Strength MPa (ksi)	Tensile Strength MPa (ksi)	Elongation (%)	Charpy V-Notch J (ft*lb f)	
					@0°C (32°F)	@20°C (68°F)
Typical Results <sup>(a)</sup> OE-S1 CrMo91	As- Welded	≥ 540 (78)	620-760 (90-110)	≥ 17	≥ 27 (20)	≥ 50 (37)
OE-S1 CrMo92	As- Welded	≥ 540 (78)	620-760 (90-110)	≥ 17	—	≥ 50 (37)

### FLUX COMPOSITION

	%CaO+MgO	%Al <sub>2</sub> O <sub>3</sub> +MnO	%CaF <sub>2</sub>	%SiO <sub>2</sub> +TiO <sub>2</sub>
OP 90W	40	25	20	10

IMPORTANT: SPECIAL VENTILATION AND/OR EXHAUST REQUIRED
Fumes from the normal use of some welding products can contain significant quantities of components - such as chromium and manganese - which can lower the 5.0 mg/m³ maximum exposure guideline for general welding fume.
BEFORE USE, READ AND UNDERSTAND THE SAFETY DATA SHEET (SDS) FOR THIS PRODUCT AND SPECIFIC INFORMATION PRINTED ON THE PRODUCT CONTAINER.

*Safety Data Sheets (SDS) and Certificates of Conformance are available on our website at [www.lincolnelectric.com](http://www.lincolnelectric.com)*

FUMES AND GASES can be hazardous to your health.

- Fumes from the normal use of this product contain significant quantities of potentially hazardous compounds. See consumable product label/insert.
- Keep your head out of the fumes.
- Use enough ventilation and local exhaust to keep fumes and gases from your breathing zone and the general area.
- An approved respirator should be used unless exposure assessments are below applicable exposure limits.

#### TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application.

#### CUSTOMER ASSISTANCE POLICY

The Lincoln Electric Company is manufacturing and selling high quality welding equipment, consumables, and cutting equipment. Our challenge is to meet the needs of our customers and to exceed their expectations. On occasion, purchasers may ask Lincoln Electric for information or advice about their use of our products. Our employees respond to inquiries to the best of their ability based on information provided to them by the customers and the knowledge they may have concerning the application. Our employees, however, are not in a position to verify the information provided or to evaluate the engineering requirements for the particular weldment. Accordingly, Lincoln Electric does not warrant or guarantee or assume any liability with respect to such information or advice. Moreover, the provision of such information or advice does not create, expand, or alter any warranty on our products. Any express or implied warranty that might arise from the information or advice, including any implied warranty of merchantability or any warranty of fitness for any customers' particular purpose is specifically disclaimed.

Lincoln Electric is a responsive manufacturer, but the selection and use of specific products sold by Lincoln Electric is solely within the control of, and remains the sole responsibility of the customer. Many variables beyond the control of Lincoln Electric affect the results obtained in applying these types of fabrication methods and service requirements.

Subject to Change – This information is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.com](http://www.lincolnelectric.com) for any updated information.

Publication C15.10.27 | Issue Date 04/23

© Lincoln Global, Inc. All Rights Reserved.

All trademarks and registered trademarks are the property of their respective owners.

THE LINCOLN ELECTRIC COMPANY  
22801 St. Clair Avenue ■ Cleveland, OH ■ 44117-1199 ■ U.S.A.  
Phone: +1.216.481.8100 ■ [www.lincolnelectric.com](http://www.lincolnelectric.com)

