

LNM 20

TOP FEATURES

- Deposit insensitive to cracking.
- Good radiographic quality.

TYPICAL APPLICATIONS

- Oil & Gas
- Thermal Power
- Pressure vessels
- Chemical
- Boilers, plates, tubes steels

CLASSIFICATION

AWS A5.28 ER90S-G*
EN ISO 21952-A G CrMo2Si

*Nearest classification ER90S-B3

SHIELDING GASES (ACC. EN ISO 14175)

M21 Mixed gas Ar+ 15-25% CO₂
C1 Active gas 100% CO₂
M13 Mixed gas Ar+ 0.5-3% O₂

APPROVALS

CE

+

CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, WIRE

C	Mn	Si	Cr	Mo
0.08	0.9	0.6	2.5	1.0

MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition*	Yield strength (MPa)	Tensile strength (MPa)	Elongation (%)	Impact ISO-V (J) +20°C
Typical values	M21	PWHT 690°C/1h	560	680	20	100

* PWHT = Post Weld Heat Treatment

PACKAGING AND AVAILABLE SIZES

Wire diameter (mm)	Packaging	Weight (kg)	Item number
1.0	SPOOL (BS300)	15.0	581164
1.2	SPOOL (BS300)	15.0	581157

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing. Please refer to www.lincolnelectric.eu for any updated information.