

# Outershield® 81K2-HSR

## TOP FEATURES

- Specific design for stress relieved applications, guaranteed impact properties after PWHT
- Superior weldability, low spatter, good bead appearance and outstanding operators appeal
- Exceptional mechanical properties (CVN >80J at -60°C)
- Superior product consistency with optimal alloy control

## TYPICAL APPLICATIONS

- Applications requiring PWHT
- Steel construction

## CLASSIFICATION

AWS A5.29 E81T1-K2M-J  
EN ISO 17632-A T 50 6 1.5Ni P M 2 H5

## CURRENT TYPE

DC+

## WELDING POSITIONS

All except vertical down

## SHIELDING GASES (ACC. EN ISO 14175)

M21 Mixed gas Ar+ (>15-25%) CO<sub>2</sub>  
Flow rate 15-25 l/min

## CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, ALL WELD METAL

Shielding gas	C	Mn	Si	P	S	Ni	HDM
M21	0.06	1.3	0.3	0.012	0.010	1.4	3 ml/100 g

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition*	Yield strength (MPa)	Tensile strength (MPa)	Elongation (%)	Impact ISO-V (J)		
						-40°C	-50°C	-60°C
Required: AWS A5.29			min. 470	550-690	min. 19	min. 27		
EN ISO 17632-A			min. 500	560-720	min. 18			min. 47
Typical values	M21	AW	590	630	23	140	100	80
		SR 1h/600°C, 3G up - V45°	570	620	23			85

\* AW = As welded; SR = Stress relieved

## PACKAGING AND AVAILABLE SIZES

Wire diameter (mm)	Packaging	Weight (kg)	Item number
1.2	SPOOL (B300)	16.0	943207N

## TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing.  
Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information.