

EXTRA

TOP FEATURES

- Excellent for root pass and positional welding.
- ISO-V toughness at -40°C.
- Deposit free from porosity and good of X-ray quality.
- The double coating confers a stable and concentrated arc with good gap bridging characteristics.

TYPICAL APPLICATIONS

- Metal construction, workshop and maintenance welding

CLASSIFICATION

| | |
|---------------|-----------------|
| AWS A5.1 | E7016-H8 |
| EN ISO 2560-A | E 42 4 B 32 H10 |

CURRENT TYPE

AC; DC+

WELDING POSITIONS

All position, except vertical down

APPROVALS

| ABS | LR | BV | DNV | TÜV | DB |
|-----|----|----|-----|-----|----|
| + | + | + | + | + | + |

CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, ALL WELD METAL

| C | Mn | Si | P | S |
|------|-----|------|--------|--------|
| 0.08 | 1.3 | 0.45 | ≤0.025 | ≤0.015 |

MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

| | Condition* | Yield strength (MPa) | Tensile strength (MPa) | Elongation (%) | Impact ISO-V (J) -40°C |
|----------------|------------|----------------------|------------------------|----------------|------------------------|
| AWS A5.1 | AW | ≥400 | ≥490 | ≥22 | not specified |
| EN ISO 2560-A | AW | ≥420 | 500-640 | ≥20 | ≥47 |
| Typical values | AW | 510 | 595 | 28 | 63 |

* AW = As welded

OUTPUT RANGE

| Diameter x Length (mm) | Current range (A) |
|------------------------|-------------------|
| 2.5x350 | 60-90 |
| 3.2x350 | 90-140 |
| 4.0x450 | 135-190 |

PACKAGING AND AVAILABLE SIZES

| Diameter x Length (mm) | Packaging | Electrodes/pack | Net weight/pack (kg) | Item number |
|------------------------|-----------|-----------------|----------------------|-------------|
| 2.5x350 | CBOX | 200 | 3.9 | W000287365 |
| 3.2x350 | CBOX | 125 | 4.1 | W000287366 |
| 4.0x450 | CBOX | 80 | 5.1 | W000287367 |

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing.
Please refer to www.lincolnelectric.eu for any updated information.