

INOXCORED 316LV

TOP FEATURES

- Alloyed rutile flux cored wire with a fast-freezing slag for positional welding of corrosion resistant 316 Cr-Ni-Mo steels.
- INOXCORED 316LV exhibits outstanding, almost spatter-free, welding properties with very easy slag removal. Designed for welding in the horizontal (PD), overhead (PE) and vertical-up (PF) positions.
- INOXCORED 316LV delivers welds with high corrosion resistance due to low carbon and balanced chemical composition.
- The best quality of welds with standard CV power sources helps to reduce investment expenditures.
- High productivity generates savings in total welding costs. Optimal semiautomatic process with high duty cycle. Application of standard Ar/CO₂ or CO₂ shielding gases optimizes welding cost.
- Savings in total welding cost resulting from reduced cleaning. Spatter free welds with easy slag removal.

CLASSIFICATION

AWS A5.22	E316LT1-1 E316LT1-1
EN ISO 17633-A	T 19 12 3 L P M21 1 T 19 12 3 L P C1 1
EN ISO 17633-B	TS316L-FB1

CURRENT TYPE

DC+

WELDING POSITIONS

All positions

SHIELDING GASES (ACC. EN ISO 14175)

M21	Mixed gas Ar+ 15-25% CO ₂
C1	Active gas 100% CO ₂

APPROVALS

LR	DNV	RINA	TÜV
+	+	+	+

CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, ALL WELD METAL

C	Mn	Si	Cr	Ni	Mo	Ferrite
≤0.04	1.5	0.6	19	12	2.8	5-10

MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition*	Yield strength (MPa)	Tensile strength (MPa)	Elongation (%)	Impact ISO-V (J)	
						+20°C	-110°C
Typical values	M21	AW	≥320	≥510	≥30	≥47	≥27

* AW = As welded

Gas test: 82% Ar + 18% CO₂

PACKAGING AND AVAILABLE SIZES

Wire diameter (mm)	Packaging	Weight (kg)	Item number
1.2	SPOOL (S200)	4.5	W000281761
	SPOOL (BS300)	15.0	W000281762

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing.
Please refer to www.lincolnelectric.eu for any updated information.