

E16.8.2-15

TOP FEATURES

- Basic pipe welding electrode for 3XXH stainless steel
- High resistance to thermal embrittlement
- Excellent toughness at low temperatures
- Recovery is about 115%

TYPICAL APPLICATIONS

- Power Generation
- Process Industries
- Process Piping

CLASSIFICATION

AWS A5.4 E16-8-2-15

CURRENT TYPE

DC+

WELDING POSITIONS

All except vertical down

CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, ALL WELD METAL

	C	Mn	Si	S	P	Cr	Ni	Mo*	Cu	FN
Min.	0.04	0.5	not specified	not specified	not specified	14.5	7.5	1.0	not specified	1
Max.	0.08	2.5	0.60	0.025	0.03	16.5	9.5	2.0	0.75	6
Typical	0.05	1.8	0.3	0.01	0.02	15.5	8.5	1.2	0.05	3

* ISO 3581 E16 8 2 B 4 2 has Mo 1.50 – 2.50%

Mo controlled around 1.0 – 1.3% unless requested otherwise.

MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

As-welded		Min.	Typical	High Temperature		
				650°C	732°C	816°C
Tensile strength	(MPa)	550	> 660	294	230	165
0.2% Proof strength	(MPa)	320	430	216	187	132
Elongation (%)	4d	35	40	-	-	-
	5d	25	37	27	36	57
Reduction of area (%)		not specified	35	61	70	75
Impact ISO-V (J)	+20°C	not specified	110 (1.8)	-	-	-
	-20°C	not specified	95 (1.6)	-	-	-
	-100°C	not specified	50 (1.0)	-	-	-

OUTPUT RANGE

Diameter x Length (mm)	Current range (A)
2.5 x 300	60-90
3.2 x 350	75-120
4.0 x 350	100-155

PACKAGING AND AVAILABLE SIZES

Diameter x Length (mm)	Packaging	Electrodes/pack	Net weight/pack (kg)	Item number
2.5 x 300	VPMD	110	1.9	E168215-25-2
3.2 x 350	VPMD	58	2.0	E168215-32-2
4.0 x 350	VPMD	40	2.1	E168215-40-2

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing.
Please refer to www.lincolnelectric.eu for any updated information.