Arosta® 304L

TOP FEATURES

- Excellent corrosion resistance in oxidizing environments such as nitric acid.
- High resistance to intergranular corrosion.
- Smooth bead appearance.
- Easy slag release.
- Strong electrode coating.
- Weldable on AC and DC.

CLASSIFICATION

AWS A5.4 E308L-16 EN ISO 3581-A E 19 9 L R 12

CURRENT TYPE

AC/DC(+/-)

WELDING POSITIONS

All position, except vertical down

APPROVALS

BV	TÜV
+	+

CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, ALL WELD METAL

С	Mn	Si	Cr	Ni	FN (acc. WRC 1992)
0.02	0.8	0.8	19.5	9.7	4-10

MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	C4:4:*	0.2% Proof strength	Tensile strength	Elongation	Impact ISO-V (J)		
	Condition*	(MPa)	(MPa)	(%)	+20°C	-20°C	-196°C
Required: AWS A5.4		not specified	min. 520	min. 35	not specified		
EN ISO		min. 320	min. 510	min. 30	not specified		
Typical values	AW	440	580	43	70	60	24

AW = As welded

OUTPUT RANGE

Diameter x Length (mm)	Current range (A)
2.0 x 300	30-50
2.5 x 350	40-75
3.2 x 350	60-110
4.0 x 350	80-150
5.0 x 350	140-220

PACKAGING AND AVAILABLE SIZES

Diameter x Length (mm)	Packaging	Electrodes/pack	Net weight/pack (kg)	Item number
2.5 x 350	СВОН	92	2.0	527537-2
3.2 x 350	CBOX	120	4.2	527834-2
4.0 x 350	CBOX	85	5.8	527940-2

Arosta® 304L-EN-11/04/24



TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing. Please refer to www.lincolnelectric.eu for any updated information.

Arosta® 304L-EN-11/04/24

