INERTROD 316LSI

TOP FEATURES

- The higher Si level results in a smooth weld bead shape and even appearance with excellent toe blending particularly in fillet welds.
- The weld metal has a high resistance to pitting and crevice corrosion by non-oxidising acids.
- Used for applications with service temperatures <400°C.

CLASSIFICATION

AWS A5.9 ER316LSi EN ISO 14343-A W 19 12 3 L Si

SHIELDING GASES (ACC. EN ISO 14175)

Inert gas Ar (100%)

TYPICAL APPLICATIONS

- Pipework
- Plates fabrication
- Shipbuilding

APPROVALS

ΤÜV	DB	CE
+	+	+

CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, WIRE

С	Mn	Si	Р	S	Cr	Ni	Мо
0.02	1.4	0.85	≤0.025	≤0.020	19	12.5	2.6

MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Chielding gas	Condition*	Yield strength (MPa)	Tensile strength (MPa)	Elongation (%)	Impact ISO-V (J)	
	Shielding gas					20°C	-120°C
Typical values	I1	AW	≥350	≥510	≥30	≥80	≥32

^{*} AW = As welded

PACKAGING AND AVAILABLE SIZES

Diameter x Length (mm)	Packaging	Weight (kg)	Item number
1.0	PE Tube	5.0	W000370407
1.2	PE Tube	5.0	W000275416
1.6	PE Tube	5.0	W000283460
2.0	PE Tube	5.0	W000283461
2.4	PE Tube	5.0	W000283462
3.2	PE Tube	5.0	W000275417



TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing. Please refer to www.lincolnelectric.eu for any updated information.

