

ER80S-B2 MIG

TOP FEATURES

- Solid wire for MIG welding 1¼Cr-½Mo creep resisting steels
- Copper coated
- Precision layer wound

CLASSIFICATION

AWS A5.28 ER80S-B2
EN ISO 21952-B G 1CM

SHIELDING GASES (ACC. EN ISO 14175)

M12 (Ar-5% CO₂) or M21 (Ar-20%CO₂)

CHEMICAL COMPOSITION (WEIGHT %), WIRE

	C	Mn	Si	S	P	Cr	Mo	Ni	Cu
Min.	0.07	0.4	0.4			1.2	0.4		
Max.	0.12	0.7	0.7	0.020	0.020	1.5	0.65	0.2	0.35
Typical	0.10	0.5	0.5	0.01	0.015	1.3	0.5	<0.1	0.10

MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

Properties after PWHT 620°C/1h	Min.	Typical	
		700°C/1h	690°C/4h
Tensile strength (MPa)	550	635	590
0.2% Proof strength (MPa)	470	530	480
Elongation (%) 4d	19	23	26
	5d	17	24
Impact ISO-V (J) +20°C		160	
	-10°C		>115
Hardness (HV)			195
	(HB)		190

PACKAGING AND AVAILABLE SIZES

Wire diameter (mm)	Packaging	Weight (kg)	Item number
0.8	SPOOL (S300)	15.0	MER80SB2-08
1.0	SPOOL (S300)	15.0	MER80SB2-10
1.2	SPOOL (S300)	15.0	MER80SB2-12

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing. Please refer to www.lincolnelectric.eu for any updated information.