

FLUXOFIL 54

TOP FEATURES

- FLUXOFIL 54 is a seamless copper coated basic flux cored wire for the hardfacing of wear parts
- 37-42 HRC hardness.

TYPICAL APPLICATIONS

- Hardfacing.

CLASSIFICATION

EN ISO 14700 T ZFe7

CURRENT TYPE

DC+

WELDING POSITIONS

Flat/Horizontal

SHIELDING GASES (ACC. EN ISO 14175)

C1 Active gas 100% CO₂

CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, ALL WELD METAL

C	Mn	Si	Cr	Mo
0.07	1.6	0.3	6	0.9

MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition*	Hardness (HRC)
Typical values	C1	AW	37-42

* AW = As welded

PACKAGING AND AVAILABLE SIZES

Wire diameter (mm)	Packaging	Weight (kg)	Item number
1.6	SPOOL (B300)	16.0	W000281348
2.4	SPOOL (B300)	16.0	W000129066

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing. Please refer to www.lincolnelectric.eu for any updated information.