

# LNM Ni2.5

## TOP FEATURES

- Ideal for low temperature applications.
- Excellent mechanical characteristic both when welded and after stress relieving.
- High impact value at low temperature (-60°C as welded and -90°C after stress relieving 15h/580°C).

## TYPICAL APPLICATIONS

- LNG
- Cryogenic Applications

## CLASSIFICATION

AWS A5.28 ER80S-Ni2  
EN ISO 14341-A G46 6 M21 2Ni2

## SHIELDING GASES (ACC. EN ISO 14175)

M21 Mixed gas Ar+ 15-25% CO<sub>2</sub>

## APPROVALS

CE

+

## CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, WIRE

C	Mn	Si	Ni
0.1	1.1	0.55	2.4

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition*	Yield strength (MPa)	Tensile strength (MPa)	Elongation (%)	Impact ISO-V (J) -60°C
Typical values	M21	AW	490	580	24	85

\* AW = As welded

## PACKAGING AND AVAILABLE SIZES

Wire diameter (mm)	Packaging	Weight (kg)	Item number
1.0	SPOOL (BS300)	15.0	580372
1.2	SPOOL (BS300)	15.0	583632

## TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information.

LNM Ni2.5-EN-20/03/24