# Limarosta® 304L

# **TOP FEATURES**

- Mirror like bead appearance
- Self releasing slag
- Excellent side wall wetting, no undercut
- High resistance to porosity
- Weldable on AC and DC

#### CLASSIFICATION

AWS A5.4 E308L-17 EN ISO 3581-A E 19 9 L R 12

# **CURRENT TYPE**

AC / DC (+/-)

# WELDING POSITIONS

All position, except vertical down

#### **APPROVALS**

LR	DNV/GL	TÜV	DB
+	+	+	+

# CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, ALL WELD METAL

С	Mn	Si	Cr	Ni	FN (acc.WRC 1992)
0.025	0.75	0.95	19.0	9.7	4-10

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Condition*	0.2% Proof strength	Tensile strength	Elongation	Impact ISO-V (J)	
	Condition	(MPa)	(MPa)	(%)	+20°C	-20°C
Required: AW	'S A5.4	not specified	min. 520	min. 35	not specified	
	EN ISO	min. 320	min. 510	min. 30	not specified	
Typical	values AW	440	600	45	75	60

AW = As welded

#### **OUTPUT RANGE**

Diameter x Length (mm)	Current range (A)
2.0 x 300	35-50
2.5 x 350	45-80
3.2 x 350	80-115
4.0 x 450	100-155
5.0 x 450	150-220

#### PACKAGING AND AVAILABLE SIZES

Diameter x Length (mm)	Packaging	Pieces / unit	Weight (kg)	ltem number
2.0x300	СВОН	150	1.8	557312-1
2.5x350	СВОН	92	2.0	557329-1
3.2x350	CBOX	120	4.2	557367-1
4.0x450	CBOX	85	5.8	557398-1
5.0x450	CBOX	50	5.3	557404-1

Limarosta® 304L-EN-01/07/22



## TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing. Please refer to <u>www.lincolnelectric.eu</u> for any updated information.

Limarosta® 304L-EN-01/07/22

