

OE-SD3 1Ni 1/4Mo

TOP FEATURES

- 1% Nickel and 0,25% Molybdenum wire to combine high strength and high toughness properties
- Impact toughness properties down to -60°C.
- Actual (Type 3.1) certificates for each lot of wire showing chemical composition are available.
- Comply with NACE requirement.

CLASSIFICATION

AWS A5.23	ENi5
EN ISO 14171-A	S3Ni1Mo0,2

CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, WIRE

C	Mn	Si	P	S	Ni	Mo
0.1	1.5	0.20	<0.015	<0.015	0.95	0.25

PACKAGING AND AVAILABLE SIZES

Wire diameter (mm)	Packaging	Weight (kg)	Item number
2.4	SPOOL	25.0	OE14MO-24-25VCI
3.2	SPOOL	25.0	OE14MO-32-25VCI
	SPOOL	100.0	OE14MO-32-100
4.0	SPOOL	25.0	OE14MO-4-25VCI
	DRUM	300.0	OE14MO-4-300, OE14MO-4-300E, OE14MO-4-300E-CCW
	DRUM	350.0	OE14MO-4-350E-CCW

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing.
Please refer to www.lincolnelectric.eu for any updated information.