

ULTRACORE® 316L P

Stainless | AWS E316T1-1, E316T1-4, E316LT1-1, E316LT1-4

KEY FEATURES

- Precision layer wound winding delivers steady spool payoff and more consistent feeding
- Smooth arc action with minimal spatter reduces post-weld cleaning
- Polished weld bead appearance reduces post-weld brushing

WELDING POSITIONS

All Positions

RECOMMENDED FLUX

N/A

CONFORMANCES

AWS A5.22/A5.22M:2012

AWS E316T1-1, E316T1-4,
E316LT1-1, E316LT1-4

TYPICAL APPLICATIONS

- 1.5 – 3% Mo austenitic stainless steel
- Suitable for Ti or Nb stabilized and nitrogen-bearing versions of the above alloys
- Applications requiring good resistance to pitting and general corrosion

SHIELDING GAS

FCAW-G: 75% Ar/25% CO₂
100% CO₂

DIAMETERS / PACKAGING

Diameter in (mm)	10 lb (4.5 kg) Plastic Spool (Vacuum Sealed Foil Bag)	33 lb (15 kg) Plastic Spool (Vacuum Sealed Foil Bag)
0.045 (1.1)	ED037221	ED037129
1/16 (1.6)	—	ED037130

MECHANICAL PROPERTIES⁽¹⁾

	Yield Strength ⁽²⁾ MPa (ksi)	Tensile Strength MPa (ksi)	Elongation %	Ferrite Number
Requirements				
AWS E316LT1-1, E316LT1-4	Not Specified	520 (75) min	30 min	Not Specified
AWS E316T1-1, E316T1-4	Not Specified	550 (80) min	30 min	Not Specified
Typical Results⁽³⁾				
As-Welded with 100% CO ₂	414 (60)	552 (80)	34	6-8
As-Welded with 75% Ar/25% CO ₂	421 (65)	565 (82)	34	8-11

⁽¹⁾Typical all weld metal, DC+ ⁽²⁾Measured with 0.2% offset ⁽³⁾See test results disclaimer

DEPOSIT COMPOSITION⁽¹⁾

	%C ⁽⁴⁾	%Mn	%Si	%S	%P
Requirements					
AWS E316LT1-1 & E316LT1-4	0.04 max	0.5-2.5	1.0 max	0.03 max	0.04 max
Typical Results⁽³⁾					
As-Welded with 100% CO ₂	≤0.03	1.0	0.6	≤0.01	≤0.02
As-Welded with 75% Ar/25% CO ₂	≤0.03	1.1	0.7	≤0.01	≤0.02
	%Ni	%Cr	%Mo	%Cu	%Bi
Requirements					
AWS E316LT1-1 & E316LT1-4	11.0-14.0	17.0-20.0	2.0-3.0	0.75 max	—
Typical Results⁽³⁾					
As-Welded with 100% CO ₂	12.3-12.5	18.0-18.5	2.5-2.8	≤0.25	0.01
As-Welded with 75% Ar/25% CO ₂	12.3-12.5	18.5-19.0	2.5-2.8	≤0.25	0.01

⁽¹⁾Typical all weld metal, DC+ ⁽³⁾See test results disclaimer ⁽⁴⁾Requirement for E316T1-1 and E316T1-4 is 0.08% max. carbon

TYPICAL OPERATING PROCEDURES

Diameter, Polarity, Shielding Gas in (mm)	CTWD ⁽⁵⁾ mm (in)	Wire Feed Speed/Voltage m/min (in/min)	Voltage (Volts)	Approx. Current (Amps)	Melt-Off Rate kg/hr (lb/hr)	Deposition Rate kg/hr (lb/hr)	Efficiency (%)
0.045 in (1.1 mm), DC+ 75% Ar/25% CO ₂	19 (3/4)	5.1 (200)	22-24	130	2.0 (4.5)	1.5 (3.3)	73.3
	19 (3/4)	8.4 (330)	24-26	180	3.3 (7.3)	2.6 (5.8)	79.4
	19 (3/4)	11.2 (440)	26-28	220	4.4 (9.7)	3.6 (7.9)	81.4
1/16 in (1.6 mm), DC+ 75% Ar/25% CO ₂	25 (1)	3.6 (140)	24-26	170	2.6 (5.7)	2.2 (4.8)	84.2
	25 (1)	5.0 (195)	24-26	200	3.6 (7.9)	3.0 (6.7)	84.8
	25 (1)	7.1 (280)	25-27	220	5.2 (11.4)	4.4 (9.7)	85

⁽⁵⁾To estimate ESO, subtract 1/4 in (6.0 mm) from CTWD. NOTE: Increase Voltage by 2V when using 100% CO₂

Safety Data Sheets (SDS) and Certificates of Conformance are available on our website at www.lincolnelectric.com

FUMES AND GASES can be hazardous to your health.

- Fumes from the normal use of this product contain significant quantities of potentially hazardous compounds. See consumable product label/insert.
- Keep your head out of the fumes.
- Use enough ventilation and local exhaust to keep fumes and gases from your breathing zone and the general area.
- An approved respirator should be used unless exposure assessments are below applicable exposure limits.

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application.

CUSTOMER ASSISTANCE POLICY

The Lincoln Electric Company is manufacturing and selling high quality welding equipment, consumables, and cutting equipment. Our challenge is to meet the needs of our customers and to exceed their expectations. On occasion, purchasers may ask Lincoln Electric for information or advice about their use of our products. Our employees respond to inquiries to the best of their ability based on information provided to them by the customers and the knowledge they may have concerning the application. Our employees, however, are not in a position to verify the information provided or to evaluate the engineering requirements for the particular weldment. Accordingly, Lincoln Electric does not warrant or guarantee or assume any liability with respect to such information or advice. Moreover, the provision of such information or advice does not create, expand, or alter any warranty on our products. Any express or implied warranty that might arise from the information or advice, including any implied warranty of merchantability or any warranty of fitness for any customers' particular purpose is specifically disclaimed.

Lincoln Electric is a responsive manufacturer, but the selection and use of specific products sold by Lincoln Electric is solely within the control of, and remains the sole responsibility of the customer. Many variables beyond the control of Lincoln Electric affect the results obtained in applying these types of fabrication methods and service requirements.

Subject to Change – This information is accurate to the best of our knowledge at the time of printing. Please refer to www.lincolnelectric.com for any updated information.

All trademarks and registered trademarks are the property of their respective owners.