


# VdTÜV-Kennblatt for welding consumables

		1 Manufacturer/Supplier ASKAYNAK TUR Istanbul		2 No. of VdTÜV-Kennblatt: 12335.02 11.2013	
3 Welding consumable*:		Stabelektrode			
4 Trade name*:		AS P - 316L Super			
7 Type*:		EN ISO 3581-A - E 19 12 3 LR 1 2			
11 Diameter range:		3,2 bis 4,0 mm			
12 Auxiliary materials:		---			
13 The validity of this Kennblatt will be certified, respectively, in the latest edition of CD-ROM TÜV-eignungsgeprüfte Schweißzusätze					
15 Materials and postweld heat treatment					
Pos	Wb	Group / Material 1	Text	Group / Material 2	Remarks
	U	Gruppe 8.1			
16 Material groups acc. to CR ISO 15608					
21 Root weldability:		not verified			
23 Wall thickness:		max. 30 mm			
24 Type of current and polarity:		G+, W			
25 Welding position according to DIN EN ISO 6947:1997-05: PA, PB, PC					
26 Highest operating temperature in the short-term range as for parent metal, but not higher than:					350°C
27 Highest operating temperature in the long-term range max.:					--- °C
28 Lowest operating temperature/as for parent metal, but not lower than:					-60°C
29 Design stress value/as for parent metal:			wie Grundwerkstoff		
30 For use in the long-term range:			---		
31 Resistance to intergranular corrosion proven in accordance with:			---		
32 Remarks: ---					
33 The approval test was done on the basis of VdTÜV-Merkblatt 1153. Where nothing different is said under the heading -Remarks-, this welding consumable is suitable provided Annex I Point 4 of the Pressure Equipment Directive 97/23/EC is observed.					
34 Explanations		A tempered L solution annealed and quenched N normalized	S stress-relieved St stabilized U non-annealed V hardened and tempered	W soft annealed	G+ direct current plus pole G- direct current minus pole W alternating current
35 Compiled in accordance with the data of:				TÜV NORD	
The duplication, circulation, copy and complete edition by photomechanical or similar techniques remain subject to the editor's approval even if only used in extracts. Editor: Verband der TÜV e. V. Distribution: TÜV-Media GmbH, Am Grauen Stein, 51105 Köln - Unternehmensgruppe TÜV Rheinland Group					