

ULTRACORE® HD-C

Mild Steel, All Position ■ AWS E71T-9C-H8, E71T1-C1A2-CS1-H8



KEY FEATURES

- High deposition rates, increase weld deposition exceeding 10 lbs/hr out-of-position
- Fast freezing slag for a flat bead shape and increased productivity in all positions, including vertical up
- Operators can set the machine on a single setting and weld in all positions
- Little or no pre-weld clean up required, weld over light rust, mill scale, and primer
- Meets AWS D1.8 seismic lot waiver requirements

WELDING POSITIONS

All

CONFORMANCES

AWS A5:	E71T1-C1A2-CS1-H8, E71T-1C-H8, E71T-9C-H8
ABS:	3YSA H10
CWB/CSA:	E491T-12MJ-H8, E491T1-M21A4-CS2-H8
DNV:	III YMS H10
Lloyd's Register:	3YS H10
ISO:	T49 3 T1-1 C1 A H10
AWS D1.8:	0.045", 0.052", 1/16"

TYPICAL APPLICATIONS

- Shipbuilding
- General fabrication

SHIELDING GAS

100% CO₂
Flow Rate: 40 - 50 CFH

DIAMETERS / PACKAGING

Diameter in (mm)	15 lb (6.8 kg) Plastic Spool 60 lb (27.2 kg) Master Carton	33 lb (15 kg) Spool**	50 lb (22.7 kg) Fiber Spool	50 lb (22.7 kg) Coil	500 lb (227 kg) Accu-Trak® Drum
0.045 (1.1)	ED033756	ED033755, ED037485*	ED033757, ED038176 *		
0.052 (1.3)	ED033759	ED033758, ED037486*	ED033760		ED034376
1/16 (1.6)	ED033762	ED033761, ED037487*	ED033763, ED037488*	ED036529*	ED033785, ED038177*

*Buy America Product **Spool may be plastic or fiber.

MECHANICAL PROPERTIES⁽¹⁾

	Yield Strength ⁽²⁾ MPa (ksi)	Tensile Strength MPa (ksi)	Elongation %	Charpy V-Notch J (ft-lbf)	
				@ -18°C (0°F)	@ -29°C (-20°F)
Requirements AWS E71T-1C-H8 AWS E71T-9C-H8	400 (58) min	480-660 (70-95)	22 min	27 (20) min Not Specified	Not Specified 27 (20) min
Test Results⁽³⁾ - As-Welded with 100% CO ₂	540-560 (78-81)	590-610 (86-89)	27	37-111 (27-82)	31-85 (23-63)

⁽¹⁾Typical all weld metal. ⁽²⁾Measured with 0.2% offset. ⁽³⁾See test results disclaimer

DEPOSIT COMPOSITION⁽¹⁾

	%C	%Mn	%Si
Requirements - AWS E71T-1C-H8, E71T-9C-H8	0.12 max	1.75 max	0.90 max
Test Results⁽³⁾ - As-Welded with 100% CO ₂	0.04-0.05	1.36-1.46	0.38-0.42
	%S	%P	Diffusible Hydrogen (mL/100g weld deposit)
Requirements - AWS E71T-1C-H8, E71T-9C-H8	0.03 max	0.03 max	8 max
Test Results⁽³⁾ - As-Welded with 100% CO ₂	0.01	0.01	4-6

TYPICAL OPERATING PROCEDURES

Diameter, Polarity Shielding Gas	CTWD ⁽⁴⁾ mm (in)	Wire Feed Speed m/min (in/min)	Voltage (Volts)	Approx. Current (Amps)	Melt-Off Rate kg/hr (lb/hr)	Deposition Rate kg/hr (lb/hr)	Efficiency (%)
0.045 in (1.1 mm), DC+ 100% CO ₂	19 - 25 (3/4 - 1)	4.4 (175)	22-25	145	1.8 (3.9)	1.5 (3.4)	85 - 87
		6.4 (250)	23-28	185	2.5 (5.6)	2.2 (4.8)	
		7.6 (300)	24-30	215	3.1 (6.8)	2.6 (5.8)	
		8.9 (350)	25-31	235	3.6 (7.9)	3.1 (6.8)	
		10.2 (400)	27-32	255	4.1 (9.0)	3.5 (7.8)	
		11.4 (450)	28-33	280	4.6 (10.1)	4.0 (8.8)	
		12.7 (500)	27-33	300	5.1 (11.3)	4.4 (9.8)	
		14.0 (550)	28-33	315	5.6 (12.4)	4.9 (10.8)	
0.052 in (1.3 mm), DC+ 100% CO ₂	19 - 25 (3/4 - 1)	3.8 (150)	22-25	155	2.1 (4.7)	1.7 (3.8)	81 - 85
		5.1 (200)	23-26	190	2.9 (6.3)	2.4 (5.2)	
		6.4 (250)	23-27	225	3.5 (7.8)	2.9 (6.5)	
		7.6 (300)	24-29	265	4.3 (9.4)	3.6 (7.9)	
		8.9 (350)	26-30	285	5.0 (11.0)	4.2 (9.2)	
		9.5 (375)	27-30	310	5.3 (11.7)	4.5 (9.9)	
		10.8 (425)	28-32	325	6.0 (13.3)	5.1 (11.2)	
		12.1 (475)	29-33	345	6.8 (14.9)	5.7 (12.6)	
1/16 in (1.6 mm), DC+ 100% CO ₂	19 - 25 (3/4 - 1)	3.8 (150)	21-26	195	2.9 (6.4)	2.4 (5.3)	84 - 87
		4.4 (175)	22-27	245	3.4 (7.5)	2.9 (6.3)	
		5.1 (200)	22-27	260	3.9 (8.5)	3.3 (7.2)	
		5.7 (225)	23-28	290	4.4 (9.6)	3.7 (8.1)	
		6.4 (250)	24-29	310	4.8 (10.6)	4.1 (9.1)	
		7.6 (300)	25-30	330	5.8 (12.7)	4.9 (10.9)	
		8.3 (325)	25-30	365	6.3 (13.8)	5.4 (11.9)	
		8.9 (350)	26-30	390	6.7 (14.8)	5.8 (12.8)	
10.2 (400)	27-31	405	7.7 (16.9)	6.7 (14.7)			

⁽¹⁾Typical all weld metal. ⁽²⁾Measured with 0.2% offset. ⁽³⁾See test results disclaimer ⁽⁴⁾As-Welded with 100% CO₂ ⁽⁵⁾To estimate ESO, subtract 1/4 in (6.0 mm) from CTWD.

Safety Data Sheets (SDS) and Certificates of Conformance are available on our website at www.lincolnelectric.com

FUMES AND GASES can be hazardous to your health.

- Fumes from the normal use of this product contain significant quantities of potentially hazardous compounds. See consumable product label/insert.
- Keep your head out of the fumes.
- Use enough ventilation and local exhaust to keep fumes and gases from your breathing zone and the general area.
- An approved respirator should be used unless exposure assessments are below applicable exposure limits.

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application.

CUSTOMER ASSISTANCE POLICY

The Lincoln Electric Company is manufacturing and selling high quality welding equipment, consumables, and cutting equipment. Our challenge is to meet the needs of our customers and to exceed their expectations. On occasion, purchasers may ask Lincoln Electric for information or advice about their use of our products. Our employees respond to inquiries to the best of their ability based on information provided to them by the customers and the knowledge they may have concerning the application. Our employees, however, are not in a position to verify the information provided or to evaluate the engineering requirements for the particular weldment. Accordingly, Lincoln Electric does not warrant or guarantee or assume any liability with respect to such information or advice. Moreover, the provision of such information or advice does not create, expand, or alter any warranty on our products. Any express or implied warranty that might arise from the information or advice, including any implied warranty of merchantability or any warranty of fitness for any customers' particular purpose is specifically disclaimed.

Lincoln Electric is a responsive manufacturer, but the selection and use of specific products sold by Lincoln Electric is solely within the control of, and remains the sole responsibility of the customer. Many variables beyond the control of Lincoln Electric affect the results obtained in applying these types of fabrication methods and service requirements.

Subject to Change – This information is accurate to the best of our knowledge at the time of printing. Please refer to www.lincolnelectric.com for any updated information.

