

FLUXOFIL 14HD

TOP FEATURES

- All positional capability with outstanding performance in vertical up welding of fillet and butt welds.
- Coefficient of flux fill and current capacity designed to deliver all positional weldability.
- Savings in welding cost resulting from easy slag removal and lack of spatters.
- Ideal for applications in shipbuilding and steel construction.
- Designed for mix gas, use of CO₂ is possible.

CLASSIFICATION

AWS A5.20	E71T-1M-JH4
EN ISO 17632-A	T 46 3 P M21 1 H5
	T 46 2 P C1 1 H5
EN ISO 17632-B	T493T1-1MAUH5

CURRENT TYPE

DC+

WELDING POSITIONS

All positions

SHIELDING GASES (ACC. EN ISO 14175)

C1	Active gas 100% CO ₂
M21	Mixed gas Ar+ 15-25% CO ₂

APPROVALS

ABS	LR	BV	DNV	RMRS	PRS	TÜV	DB
+	+	+	+	+	+	+	+

CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, ALL WELD METAL

C	Mn	Si	P	S
0.05	1.4	0.5	≤0.010	≤0.010

MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition*	Yield strength (MPa)	Tensile strength (MPa)	Elongation (%)	Impact ISO-V (J)	
						-20°C	-30°C
Typical values	M21	AW	≥460	550-650	≥24	≥80	≥50

* AW = As welded

Gas test: 82% Ar + 18% CO₂

PACKAGING AND AVAILABLE SIZES

Wire diameter (mm)	Packaging	Weight (kg)	Item number
1.0	SPOOL (S200)	5.0	W000281096
	SPOOL (B300)	16.0	W000281097
1.2	SPOOL (S200)	5.0	W000281098
	SPOOL	12.5	W000373239
	SPOOL	16.0	W000381099
	SPOOL (B300)	16.0	W000281099
	DRUM	200.0	W000281100
1.6	SPOOL (B300)	16.0	W000281105
	SPOOL (BS300)	16.0	W000381105

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing.
Please refer to www.lincolnelectric.eu for any updated information.