# **FLUXOFIL 14HDS**

## **TOP FEATURES**

- Good quality of welds, increased electrode efficiency due to low spatter loss, easy slag removal.
- Outstanding welding characteristics.
- Increased current carrying capacity and deposition rate,

#### CLASSIFICATION

AWS A5.20 E71T-1M-JH4
EN ISO 17632-A T 46 4 P M21 1 H5

## **WELDING POSITIONS**

All positions

## **SHIELDING GASES (ACC. EN ISO 14175)**

M21 Mixed gas Ar+ 15-25% CO<sub>2</sub>

#### **APPROVALS**

ABS	LR	BV	DNV	TÜV
+	+	+	+	+

# CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, ALL WELD METAL

С	Mn	Si	Ni
0.05	1.2	0.55	0.4

## **MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL**

	Shielding gas	Condition*	Yield strength (MPa)	Tensile strength (MPa)	Elongation (%)	Impact ISO-V (J) -40°C
Typical values	M21	AW	≥460	550-650	≥22	≥50

<sup>\*</sup> AW = As welded

## **PACKAGING AND AVAILABLE SIZES**

Wire diameter (mm)	Packaging	Weight (kg)	Item number
1.2	SPOOL (B300)	16.0	W000404044

## **TEST RESULTS**

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing. Please refer to <a href="www.lincolnelectric.eu">www.lincolnelectric.eu</a> for any updated information.

