

CARBOROD Mo

TOP FEATURES

- Used for welding low alloy creep resistant ferritic steels and fine grained steels.
- Ideal for low temperature applications in the as welded condition with service temperatures in range -40°C to +500°C.

TYPICAL APPLICATIONS

- Chemical plant construction
- Petrochemical
- Oil & Gas
- Thermal Power
- Nuclear

CLASSIFICATION

AWS A5.28 ER 70S-A1
EN ISO 21952-A W MoSi

SHIELDING GASES (ACC. EN ISO 14175)

I1 Inert gas Ar (100%)

APPROVALS

TÜV	CE
+	+

CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, WIRE

C	Mn	Si	P	S	Mo
0.10	1.0	0.6	≤0.020	≤0.020	0.5

MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition*	Yield strength (MPa)	Tensile strength (MPa)	Elongation (%)	Impact ISO-V (J)	
						+20°C	-40°C
Typical values	I1	AW	≥480	≥550	≥29	≥120	≥47

* AW = As welded

PACKAGING AND AVAILABLE SIZES

Diameter x Length (mm)	Packaging	Weight (kg)	Item number
1.2	PE Tube	5.0	W000283352
1.6	PE Tube	5.0	W000283353
2.0	PE Tube	5.0	W000283354
2.4	PE Tube	5.0	W000283355
3.2	PE Tube	5.0	W000283356

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing.
Please refer to www.lincolnelectric.eu for any updated information.