

STARINOX 316L

TOP FEATURES

- Excellent operability and is particularly suitable for downhand butt and fillet welding applications, the 2.5mm and 3.2mm diameter electrodes can be used for positional welding.
- Combines a stable spray arc transfer resulting in excellent weld bead shape and appearance with a slight concave profile in horizontal vertical fillet welds. There is very little spatter and in combination with the self-releasing slag, post welding cleaning time is maintained to a minimum.
- Suitable for use with either AC [minimum OCV 50V] or DC positive.

CLASSIFICATION

AWS A5.4 E316L-16
EN ISO 3581-A E 19 12 3 L R 12

CURRENT TYPE

AC, DC+

WELDING POSITIONS

All positions

APPROVALS

ABS	LR	BV	DNV	RINA	TÜV	DB	CE
+	+	+	+	+	+	+	+

CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, ALL WELD METAL

C	Mn	Si	P	S	Cr	Ni	Mo	Ferrite
0.035	0.9	0.8	≤0.025	≤0.025	19.0	12.0	2.6	5-10

MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

Required	Condition*	0.2% Proof strength (MPa)	Tensile strength (MPa)	Elongation (%)	Impact ISO-V (J) +20°C
AWS A5.4	AW	not specified	≥490	≥30	not specified
EN ISO 3581-A	AW	≥320	≥510	≥25	not specified
Typical values	AW	≥350	≥510	≥30	≥50

* AW: As-welded

OUTPUT RANGE

Diameter x Length (mm)	Current range (A)
2.0 x 300	30-60
2.5 x 300	55-80
3.2 x 350	70-110
4.0 x 350	120-140
5.0 x 350	145-180

PACKAGING AND AVAILABLE SIZES

Diameter x Length (mm)	Packaging	Electrodes/pack	Net weight/pack (kg)	Item number
2.0 x 300	VPMD	150	1.7	W100288785
2.5 x 350	VPMD	90	2.0	W100288786
3.2 x 350	VPMD	55	1.9	W100288788
4.0 x 450	VPMD	37	2.5	W100288789

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing.
Please refer to www.lincolnelectric.eu for any updated information.