

Conarc® 55CT

TOP FEATURES

- Excellent mechanical properties (impact down to -40°C).
- Suitable for positional welding and welding with an inverter power source.
- Very low diffusible hydrogen content.
- The weld deposit has a very similar appearance to Cor-Ten A steel.

CLASSIFICATION

AWS A5.5	E8018-G H4
EN ISO 2560-A	E 50 4 Z B 32 H5

CURRENT TYPE

AC/DC(+/-)

WELDING POSITIONS

All position, except vertical down

CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, ALL WELD METAL

C	Mn	Si	P	S	Ni	Cu	Cr
0.06	1.3	0.4	≤0.02	≤0.02	0.45	0.45	0.5

MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Condition*	0.2% Proof strength (MPa)	Tensile strength (MPa)	Elongation (%)	Impact ISO-V (J)	
Required: AWS A5.5		min. 460	min. 550	min. 19	min. 27	
EN ISO 2560-A	AW	min. 500	560-720	min. 18		≥47
Typical values		≥500	560-720	≥23		100

AW = As welded

OUTPUT RANGE

Diameter x Length (mm)	Current range (A)
2.5 x 350	55-85
3.2 x 350	80-145
4.0 x 350	120-185
5.0 x 450	180-270

PACKAGING AND AVAILABLE SIZES

Diameter x Length (mm)	Packaging	Electrodes/pack	Net weight/pack (kg)	Item number
2.5 x 350	SRP	62	1.5	523522-1
3.2 x 350	SRP	50	2.0	523539-1
4.0 x 450	SRP	27	1.9	523546-1

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing.
Please refer to www.lincolnelectric.eu for any updated information.