

# LNM MoNi

## TOP FEATURES

- The weld metal contains less than 1% Ni conforming to NACE requirement.
- For welding high yield strength steels.

## TYPICAL APPLICATIONS

- Infrastructures
- Earthmoving
- Cranes
- Structural Steels

## CLASSIFICATION

AWS A5.28 ER100S-G  
EN ISO 16834-A G 62 4 M21 Mn3NiCrMo

## SHIELDING GASES (ACC. EN ISO 14175)

M21 Mixed gas Ar+ 15-25% CO<sub>2</sub>

## APPROVALS

CE

+

## CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, WIRE

C	Mn	Si	P	S	Ni	Cr	Mo	Cu	V
0.09	1.4	0.70	0.01	0.01	0.55	0.55	0.25	0.08	0.05

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition*	Yield strength (MPa)	Tensile strength (MPa)	Elongation (%)	Impact ISO-V (J)		
						-20 °C	-40 °C	-60 °C
Typical values	M21	AW	635	735	21	110	100	70

\* AW = As welded

## PACKAGING AND AVAILABLE SIZES

Wire diameter (mm)	Packaging	Weight (kg)	Item number
1.0	SPOOL (B300)	16.0	S10K016PZE01
1.2	SPOOL (B300)	16.0	S12K016PZE01

## TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information.

LNM MoNi-EN-05/03/24