# **CITOFLUX ROO**

#### **TOP FEATURES**

- CITOFLUX ROO is rutile flux cored wire for gas shielded metal arc welding of unalloyed steels.
- The optimized fill ratio results in increased deposition rate and productivity leading to savings in total welding cost.
- The weld pool is easily controllable in positional welding with outstanding arc properties and quality levels.
- Low spatter and easy slag removal result in smooth and regular welds.
- Can be used in semiautomatic and mechanized processes, very well suited for use on ceramic backing.
- Preferably used under mixed gas. The use of CO₂ is possible.

#### CLASSIFICATION

AWS A5.20 E71T-1C-H4

E71T-1M-JH4

EN ISO 17632-A T 42 2 P C1 H5

T 42 3 P M21 1 H5

EN ISO 17632-B T492T1-1CA-UH5

T493T1-1MA-UH5

#### **CURRENT TYPE**

DC+

#### **WELDING POSITIONS**

All positions

# **SHIELDING GASES (ACC. EN ISO 14175)**

C1 Active gas 100% CO₂
M21 Mixed gas Ar+ 15-25% CO₂

# **APPROVALS**

ABS	LR	BV	DNV	RINA	RMRS	CRS	PRS
+	+	+	+	+	+	+	+

# **CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, ALL WELD METAL**

С	Mn	Si	Р	S
0.05	1.47	0.5	≤0.015	≤0.015

# **MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL**

	Chialdina	Condition*	Yield strength (MPa)	Tensile strength (MPa)	Elongation (%)	Impact ISO-V (J)	
	Shielding gas	Condition				-20°C	-30°C
Typical values	M21	AW	min 420	500-640	≥28	≥80	≥50

<sup>\*</sup> AW = As welded

Gas test: 82% Ar + 18% CO<sub>2</sub>

# **PACKAGING AND AVAILABLE SIZES**

Wire diameter (mm)	Packaging		ltem number
1.2	SPOOL (B300)	16.0	W000281147



#### **TEST RESULTS**

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing. Please refer to <a href="www.lincolnelectric.eu">www.lincolnelectric.eu</a> for any updated information.

