

CERTIFICATE OF CONFORMANCE



Electrode: **Innershield® NR®-232**
 Electrode Size: **.072" (1.8 mm)**
 Specification: **AWS D1.8:2016**
 Date: **March 01, 2022**

This is to certify that the above listed product was manufactured to meet the Class T4 requirement of AWS A5.01 as required by clause 6.3.1.2 of AWS D1.8:2016.

It was manufactured and supplied according to a Quality System Program that meets the requirements of ISO9001 among others as documented on The Lincoln Electric web page (<http://www.lincolnelectric.com/en-us/company/Pages/certifications.aspx>).

Operating Settings	High Heat Input Requirements	Low Heat Input Requirements	High Heat Input Results	Low Heat Input Results
Electrode Lot			17161404	17161404
Base Material			ASTM A572 steel (Grade 50)	ASTM A572 steel (Grade 50)
Current Type/Polarity			DC-	DC-
Plate Thickness, mm (in)	(3/4)	(3/4)	19 (3/4)	19 (3/4)
Nominal Voltage, V			22	20
Wire Feed Speed, cm/min (in/min)			394 (155)	457 (180)
Nominal Current, A			250	290
Average Heat Input, kJ/mm (kJ/in)	Not Specified	Not Specified	2.9 (74.1)	1.2 (30.8)
Travel Speed, cm/min (in/min)			11 (4.5)	29 (11.3)
Contact Tip to Work Distance, mm (in)			25 (1)	25 (1)
Pass/Layers			8/5	20/7
Preheat Temperature, °C (°F)	(250 min.)	(120 max.)	135 (275)	20 (70)
Interpass Temperature, °C (°F)	(450 min.)	(250 max.)	230 (450)	120 (250)
Postweld Heat Treatment	As-welded	As-welded	As-welded	As-welded
Weld Position			3G	1G

Mechanical properties of weld deposits

Tensile Strength, MPa (ksi)	(70 min.)	(70 min.)	580 (84)	620 (90)
Yield Strength, 0.2% Offset, MPa (ksi)	(58 min.)	(58 min.)	410 (60)	490 (70)
Elongation %	22 min.	22 min.	30	27
Average Impact Energy Joules @ -18 °C (ft-lbs @ 0 °F)	(40 min.)	(40 min.)	74 (55) 74,74,76 (54,54,56)	55 (41) 52,56,58 (38,41,43)

- This product satisfies the requirements of AWS D1.8:2016, Annex E, after exposure for 1 week at 80°F / 80% relative humidity.
- This document meets the requirements of AWS A5.01M/A5.01 Schedule F. When a specific lot number is referenced it also meets the requirements of EN10204, type 2.2. It does not meet the requirements of type 3.1.
- The Charpy V-notch impact values reported at -18 °C (0 °F) are required when the Lowest Anticipated Service Temperature (LAST) is -29 °C (-20 °F).
- Lot testing exemption as defined in AWS D1.8/D1.8M: 6.3.3 by testing a minimum of 3 lots for approval has been completed. For further questions please contact customer service. <https://www.lincolnelectric.com/en/Ask-the-Experts/Contact-Us>
- The strength and elongation properties reported here were obtained from tensile specimens artificially aged at 105°C (220°F) for 48 hours.
- Strength values in SI units are reported to the nearest 10 MPa converted from actual data. Preheat and interpass temperature values in SI units are reported to the nearest 5 degrees.

Daniel Gaul, Certification Supervisor

March 01, 2022

Date

Radhika Panday, Manager, Consumable
 Compliance Designee

March 08, 2022

Date