

# Lincore<sup>®</sup> 40-0

## CLASSIFICATION

EN 14700 T Fe1

## GENERAL DESCRIPTION

Higher hardness for metal-to-metal wear and mild abrasion  
 Used on transfer rollers and guides, crane wheels and shafts  
 Can be used on low carbon and low alloy steels  
 Unlimited layers with proper preheat and interpass temperatures and procedures

## WELDING POSITIONS (ISO/ASME)



PA/1G

## CURRENT TYPE

DC+

## CHEMICAL COMPOSITION (W%), TYPICAL, ALL WELD METAL

C	Mn	Si	Cr	Al	Mo
0.2	1.5	0.7	3.5	1.8	0.4

## STRUCTURE

Martensitic

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

### Typical hardness values

Layer 1	ca. 36 HRC (340HB)
Layer 2	ca. 41 HRC (380HB)

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	2.0
11.34kg coil 22RR	X
22.68 kg coil 50C	

Lincore<sup>®</sup> 40-0: rev. C-EN23-01/02/16

# Lincore<sup>®</sup> 40-0


## APPLICATION

This electrode provides an overlay hardfacing deposit on carbon and low alloy steels that resists rolling, sliding and metal-to-metal wear under heavy impact conditions. The deposit has a hardness of about 40 HRC which fills in the rather large hardness gap between the ferritic bainite buildup deposit of Lincore 33 and the martensitic deposit from Lincore 55 designed for metal-to-metal wear. Although the electrode is designed to provide a hardfacing deposit by itself, it could be used as a build-up electrode to provide a base on which harder deposits could be overlaid.

Typical applications include:

Tractor rolls  
 Mine car wheels  
 Guide rollers  
 Bucket links and bases  
 Actuating cams

Mine car wheels



## ADDITIONAL INFORMATION

The area to be hardfaced should be clean and free of rust, scale, oil, grease or dirt of any kind. Any previous hardfacing deposit that has been embrittled by severe work hardening should also be removed. Irregularities such as cracks, low spots etc. should be properly repaired before hardfacing. Cold parts should be preheated to at least 40°C. Larger parts, and those made of higher alloy or higher carbon steel, should be preheated to the 100-150°C range.

Lincore 40-0 deposits normally have good resistance to cross-checking. Special precautions, however, should be taken with any buildup or hardfacing product on applications that are inherently crack sensitive. These applications include the facing of high carbon or alloy steels, previously faced parts and highly stressed parts. The facing of heavy cylinders, massive parts and parts having complex shapes are all examples of applications producing high internal stresses that may result in delayed cracking.

These applications may require one or more of the following:

1. Higher preheat temperature (150-260°C).
2. Higher interpass temperatures.
3. Controlled slow cooling between passes and/or layers

Interpass temperatures in the range of 150-200°C will not significantly affect the hardness of weld deposits produced by Lincore 40-0.

The weld deposited, can be machined with carbide tools or can be finished by grinding.

## CALCULATION DATA

Diameter (mm)	Wire Feed Speed (cm/min)	Current (A)	Arc Voltage (V)	Deposition rate (kg/h)	Efficiency (%)
2.0	3.2-6.4	200-325	23-29	3.1-6.1	87-86

## COMPLEMENTARY PRODUCTS

Wearshield<sup>®</sup> MM40