

# Chromet® 2X

## TOP FEATURES

- 2%Cr-1Mo deposit which meets specific requirements for improved temper embrittlement resistance after prolonged service at 400-600°C
- Relevant trace elements (P, Sn, As, Sb) are controlled to ensure low Bruscato (X) and Watanabe (J) factors
- Basic flux, metal powder type coatings on low carbon high purity core wire
- Recovery is about 115%

## TYPICAL APPLICATIONS

- Steam Generating Power Plant
- Piping
- Turbine Castings
- Valve Bodies and Boiler Superheaters
- Coal Liquefaction Plant and Pressure Vessels

## CLASSIFICATION

AWS A5.5	E9018-B3 H4R
EN ISO 3580-A	E CrMo2 B 3 2 H5
EN ISO 3580-B	E 6216-2C1M

## CURRENT TYPE

DC+/AC

## WELDING POSITIONS

All position, except vertical down

## CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, ALL WELD METAL

	C	Mn	Si	S	P	Cr	Mo	Cu	Sn	As	Sb
Min.	0.05	0.50	0.15	not specified	not specified	2.00	0.90	not specified	not specified	not specified	not specified
Max.	0.10	0.90	0.30	0.015	0.012	2.50	1.20	0.15	0.005	0.010	0.005
Typical	0.06	0.7	0.25	0.012	0.010	2.25	1.05	< 0.05	0.002	0.003	< 0.002

\*Mn+Si < 1.10%

Bruscato factor (X) :  $(10P + 5Sb + 4Sn + As \text{ (ppm)}) / 100 = 15 \text{ max}$

Watanabe factor (J) :  $(Mn+Si) \times (P + Sn) \times 104 = 180 \text{ max}$

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

Properties after PWHT:		Min.	690°C/1h	Typical 690°C/5h	690°C/5h + SC
Tensile strength	(MPa)	630	670	660	650
0.2% Proof strength	(MPa)	540	570	560	550
Elongation (%)	4d	17	22	27	25
	5d	18	19	24	20
Reduction of area (%)		not specified	65	70	65
Impact ISO-V (J)	+20°C	47 (2)	140	170	170
	-30°C	not specified	80	140	110
Hardness (HV)		not specified	220-250	195	205

(1) ISO & PWHT 690°C/1h

## OUTPUT RANGE

Diameter x Length (mm)	Current range (A)
3.2 x 350	80-140
4.0 x 450	100-180
5.0 x 450	140-240

**PACKAGING AND AVAILABLE SIZES**

Diameter x Length (mm)	Packaging	Electrodes/pack	Net weight/pack (kg)	Item number
3.2 x 350	VPMD	55	2.0	CHROMET2X-32-2
4.0 x 450	VPMD	40	2.8	CHROMET2X-40-2
5.0 x 450	VPMD	20	2.2	CHROMET2X-50-2

**TEST RESULTS**

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application.

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information.