



# Metalshield® MC® -706

Mild Steel • AWS E70C-6M H4

## Key Features

- ▶ High deposition rates and travel speed
- ▶ Enhanced silicon island management
- ▶ H4 diffusible hydrogen level
- ▶ Tolerates high amounts of surface contaminants
- ▶ Superior arc wetting and bead appearance

## Conformances

AWS A5.18/A5.18M: 2005 E70C-6M H4  
 ASME SFA-A5.18: E70C-6M H4  
 ABS: E70C-6M H4  
 CWB/CSA W48-06: E492C-6MJ-H4  
 AWS D1.8  
 FEMA 353

## Typical Applications

- ▶ Robotics/hard automation
- ▶ Structural fabrication
- ▶ Process piping and pressure vessels
- ▶ Shipbuilding
- ▶ Heavy fabrication

## Welding Positions

Flat & Horizontal

## Shielding Gas

75-95% Argon / Balance CO<sub>2</sub>  
 Flow Rate: 40-60 CFH

## DIAMETERS / PACKAGING

Diameter in (mm)	33 lb (15 kg) Steel Spool	50 lb (22.7 kg) Fiber Spool	50 lb (22.7 kg) Coil	500 lb (227 kg) Accu-Trak® Drum
0.045 (1.1)	ED031583	ED031586	ED031589	ED031592
0.052 (1.3)	ED031584	ED031587	ED031590	ED031593
1/16 (1.6)	ED031585	ED031588	ED031591	ED031594

## MECHANICAL PROPERTIES<sup>(1)</sup> – As Required per AWS A5.18/A5.18M: 2005

	Yield Strength <sup>(2)</sup> MPa (ksi)	Tensile Strength MPa (ksi)	Elongation %	Charpy V-Notch J (ft•lbf)	
				@ -29°C (-20°F)	@ -40°C (-40°F)
<b>Requirements</b> - AWS E70C-6M H4	400 (58) min.	480 (70) min.	22 min.	27 (20) min.	Not Specified
<b>Typical Results</b> <sup>(3)</sup>					
As-Welded with 75% Argon / 25% CO <sub>2</sub> <sup>(4)</sup>	450-510 (65-75)	510-590 (75-85)	24-28	96-137 (71-101)	81-111 (60-82)
As-Welded with 90% Argon / 10% CO <sub>2</sub>	480-550 (70-80)	550-620 (80-90)	24-28	57-108 (42-80)	41-94 (30-69)

**Metalshield® MC® -706**

(AWS E70C-6M H4)

**DEPOSIT COMPOSITION<sup>(1)</sup> – As Required per AWS A5.18/A5.18M: 2005**

	%C	%Mn	%Si	%S	%P	%Cu
<b>Requirements - AWS E70C-6M H4</b>	0.12 max.	1.75 max.	0.90 max.	0.03 max.	0.03 max.	0.50 max.
<b>Typical Results<sup>(3)</sup></b>						
As-Welded with 75% Argon / 25% CO <sub>2</sub> <sup>(4)</sup>	0.03-0.05	1.25-1.60	0.50-0.80	0.02-0.03	0.01-0.02	0.01-0.05
As-Welded with 90% Argon / 10% CO <sub>2</sub>	0.03-0.05	1.25-1.70	0.60-0.85	0.02-0.03	0.01-0.02	0.01-0.05
	%Ni	%Cr	%Mo	%V	%Ni + %Cr + %Mo + %V	Diffusible Hydrogen (mL/100g weld deposit)
<b>Requirements - AWS E70C-6M H4</b>	0.50 max.	0.20 max.	0.30 max.	0.08 max.	0.50 max.	≤ 4
<b>Typical Results<sup>(3)</sup></b>						
As-Welded with 75% Argon / 25% CO <sub>2</sub> <sup>(3)</sup>	0.01-0.03	0.01-0.04	0.01-0.02	0.01-0.02	0.05-0.10	2-4
As-Welded with 90% Argon / 10% CO <sub>2</sub>	0.01-0.03	0.01-0.05	0.01-0.02	0.01-0.02	0.05-0.10	

**TYPICAL OPERATING PROCEDURES**

Diameter, Polarity Shielding Gas	CTWD <sup>(5)</sup> mm (in)	Wire Feed Speed m/min (in/min)	Voltage <sup>(6)</sup> (volts)	Approx. Current (amps)	Melt-Off Rate kg/hr (lb/hr)	Deposition Rate kg/hr (lb/hr)	Efficiency (%)
<b>0.045 in (1.1 mm), DC+</b> 90% Argon / 10% CO <sub>2</sub>	19-25 (3/4-1)	5.1 (200)	21-23	155	2.3 (5.0)	2.1 ((4.6)	92
		6.4 (250)	22-24	185	2.8 (6.2)	2.6 (5.8)	94
		7.6 (300)	22-26	220	3.5 (7.7)	3.2 (7.0)	91
		8.9 (350)	22-27	245	4.0 (8.9)	3.7 (8.2)	93
		10.2 (400)	23-27	260	4.6 (10.1)	4.3 (9.4)	93
		11.4 (450)	23-28	280	5.2 (11.4)	4.9 (10.7)	94
		12.7 (500)	23-29	305	5.7 (12.6)	5.5 (12.2)	97
		14.0 (550)	24-29	315	6.3 (13.9)	6.2 (13.6)	98
		15.2 (600)	25-30	325	6.8 (15.1)	6.7 (14.8)	98
16.5 (650)	26-30	355	7.5 (16.5)	7.4 (16.3)	98		
17.8 (700)	26-30	360	8.0 (17.7)	7.9 (17.5)	99		
<b>0.052 in (1.3 mm), DC+</b> 90% Argon / 10% CO <sub>2</sub>	19-25 (3/4-1)	5.1 (200)	22-24	210	3.0 (6.7)	2.9 (6.3)	94
		6.4 (250)	22-26	260	3.9 (8.5)	3.5 (7.8)	92
		7.6 (300)	22-27	290	4.6 (10.2)	4.3 (9.5)	94
		8.9 (350)	23-27	315	5.4 (11.8)	5.2 (11.4)	97
		10.2 (400)	24-28	350	6.3 (13.8)	6.1 (13.4)	97
		11.4 (450)	25-28	370	6.9 (15.2)	6.8 (15.1)	99
		12.7 (500)	27-29	390	7.7 (16.9)	7.6 (16.8)	99
14.0 (550)	27-30	420	8.4 (18.5)	8.3 (18.3)	99		
<b>1/16 in (1.6 mm), DC+</b> 90% Argon / 10% CO <sub>2</sub>	25-32 (1-1 1/4)	3.8 (150)	22-24	230	3.2 (7.0)	2.8 (6.2)	89
		5.1 (200)	22-25	280	4.3 (9.4)	3.9 (8.7)	93
		6.4 (250)	23-28	310	5.3 (11.6)	5.0 (11.0)	94
		7.6 (300)	24-29	370	6.3 (13.9)	6.3 (13.8)	99
		8.9 (350)	26-30	400	7.4 (16.3)	7.2 (15.9)	98
		10.2 (400)	26-31	450	8.3 (18.4)	8.3 (18.4)	99
11.4 (450)	27-31	480	9.5 (21.0)	9.3 (20.6)	98		

<sup>(1)</sup>Typical all weld metal. <sup>(2)</sup>Measured with 0.2% offset. <sup>(3)</sup>See test results disclaimer below. <sup>(4)</sup>Required gas mixture 75-80% Argon/Balance CO<sub>2</sub> for AWS testing. <sup>(5)</sup>To estimate ESO, subtract 3/16 in (4.8 mm) from CTWD. <sup>(6)</sup>For greater percentage of CO<sub>2</sub> shielding gas, increase voltage by 1-2 volts. NOTE: This product contains micro-alloying elements. Additional information available upon request.

Material Safety Data Sheets (MSDS) and Certificates of Conformance are available on our website at [www.lincolnelectric.com](http://www.lincolnelectric.com)

### TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application.

### CUSTOMER ASSISTANCE POLICY

The Lincoln Electric Company is manufacturing and selling high quality welding equipment, consumables, and cutting equipment. Our challenge is to meet the needs of our customers and to exceed their expectations. On occasion, purchasers may ask Lincoln Electric for information or advice about their use of our products. Our employees respond to inquiries to the best of their ability based on information provided to them by the customers and the knowledge they may have concerning the application. Our employees, however, are not in a position to verify the information provided or to evaluate the engineering requirements for the particular weldment. Accordingly, Lincoln Electric does not warrant or guarantee or assume any liability with respect to such information or advice. Moreover, the provision of such information or advice does not create, expand, or alter any warranty on our products. Any express or implied warranty that might arise from the information or advice, including any implied warranty of merchantability or any warranty of fitness for any customers' particular purpose is specifically disclaimed.

Lincoln Electric is a responsive manufacturer, but the selection and use of specific products sold by Lincoln Electric is solely within the control of, and remains the sole responsibility of the customer. Many variables beyond the control of Lincoln Electric affect the results obtained in applying these types of fabrication methods and service requirements.

Subject to Change – This information is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.com](http://www.lincolnelectric.com) for any updated information.